

U.S. DEPARTMENT OF COMMERCE, PATENT AND TRADEMARK OFFICE		DATE: <b>October 1, 2001</b>
<b>TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371</b>		U.S. APPL. NO. (if known) <b>09/926254</b>
INTERNATIONAL APPLICATION NO.: <b>PCT/JP00/02158</b>	INTERNATIONAL FILING DATE: <b>APRIL 3, 2000</b>	PRIORITY DATE CLAIMED: <b>APRIL 2, 1999</b>
TITLE OF INVENTION: <b>METHOD OF TREATING POLYMER</b>		
APPLICANT(S) FOR DO/EO/US: <b>Yoshiki NAKAGAWA, Kenichi KITANO and Nao FUJITA</b>		

Applicant hereby submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. XX This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2.      This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. XX This express request to begin national examination procedures (35 USC 371(f)) at any time rather than delay examination until the expiration of the time limit set in 35 USC 371(b) and PCT Articles 22 and 39(1).
4. XX A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. XX A copy of the International Application as filed (35 U.S.C. 371(c)(2)):
  - is transmitted herewith (required only if not transmitted by the International Bureau).
  - XX has been transmitted by the International Bureau.
  - is not required, as the application was filed in the United States Receiving Office (RO/US)
6. XX A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. XX Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
  - are transmitted herewith (required only if not transmitted by the International Bureau).
  - have been transmitted by the International Bureau.
  - have not been made; however, the time limit for making such amendments has NOT expired.
  - XX have not been made and will not be made.
8.      A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9.      An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10.      A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

**ITEMS 11. TO 16. BELOW CONCERN OTHER DOCUMENT(S) OR INFORMATION INCLUDED:**

11.      An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12.      An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.  
ASSIGNEE NAME AND ADDRESS: **KANEKA CORPORATION, Osaka-shi, Japan**  
**Please publish the assignee data with the application.**
13. XX A **FIRST** preliminary amendment.  
     A **SECOND** or **SUBSEQUENT** preliminary amendment
14.      A substitute specification.
15.      A change of power of attorney and/or address letter.
16. XX Other items or information: International Search Report.

U.S. APPLICATION NO. (if known: <b>09/926254</b> )		INTERNATIONAL APPLICATION NO. <b>PCT/JP00/02158</b>		DATE: <b>October 1, 2001</b>	
17. <input checked="" type="checkbox"/> The following fees are submitted:				CALCULATIONS _____ PTO USE ONLY _____	
<b>Basic National Fee (37 CFR 1.492(a)(1)-(5):</b> Search Report has been prepared by the EPO or JPO: ..... \$890.00  International preliminary examination fee paid to USPTO (37 CFR 1.482) ..... \$710.00  No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2)) ..... \$740.00  Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO ..... \$1040.00  International preliminary examination fee (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(2)-(4) ..... \$100.00					
<b>ENTER APPROPRIATE BASIC FEE AMOUNT =</b>				<b>\$ 890.00</b>	
Surcharge of <b>\$130.00</b> for furnishing the oath or declaration later than __ 20 x 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				<b>\$ 130.00</b>	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
TOTAL	26-20 =	6	X \$ 18.00	<b>\$ 108.00</b>	
INDEPENDENT	1-3 =		X \$ 84.00		
Multiple dependent claims(s) (if applicable)			+ \$280.00		
<b>TOTAL OF ABOVE CALCULATIONS =</b>				<b>\$ 1,128.00</b>	
Reduction by 1/2 for filing by small entity, if applicable. (Note 37 CFR 1.9, 1.27, 1.28).					
<b>SUBTOTAL =</b>				<b>\$ 1,128.00</b>	
Processing fee of <b>\$130.00</b> for furnishing the English translation later than __ 20 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				+	
<b>TOTAL NATIONAL FEE =</b>				<b>\$ 1,128.00</b>	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). <b>\$40.00 per property +</b>					
<b>TOTAL FEES ENCLOSED =</b>				<b>\$ 1,128.00</b>	
				Amount to be: _____ refunded \$ _____ _____ charged \$ _____	

ATTORNEY'S DOCKET NO: 011300

U.S. APPLICATION NO. (if known)	INTERNATIONAL APPLICATION NO. <b>PCT/JP00/02158</b>	DATE: <b>October 1, 2001</b>
------------------------------------	--	------------------------------


a. XX A check in the amount of \$ 1,128.00 to cover the above fees is enclosed. (\$890.00 for basic filing fee; \$108.00 for 6 additional claims and \$130.00 for late filing of the declaration). (This paper is filed in triplicate)


b.        Please charge my Deposit Account No. 01-2340 in the amount of \$        to cover the above fees. (A duplicate copy of this sheet is enclosed.)

c. X The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 01-2340.

**NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed to request that the application be restored to pending status.**

**Send All Correspondence To:**

  
**23850**  
 PATENT TRADEMARK OFFICE

  
 \_\_\_\_\_  
 SIGNATURE  
 \_\_\_\_\_  
 Stephen G. Adrian  
 NAME  
 \_\_\_\_\_  
 32,878  
 REGISTRATION NUMBER

ARMSTRONG, WESTERMAN, HATTORI,  
 McLELAND & NAUGHTON, LLP  
 Suite 1000, 1725 K Street, N.W.  
 Washington, D. C. 20006  
 Tel: (202) 659-2930  
 Fax: (202) 887-0357

PATENT  
IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of: **Yoshiki NAKAGAWA et al.**

Serial No.: **Not Yet Assigned**  
(PCT/JP00/02158)

Filed: **October 1, 2001**

For: **METHOD OF TREATING POLYMER**

PRELIMINARY AMENDMENT

Commissioner for Patents  
Washington, D.C. 20231

October 1, 2001

Sir:

Prior to the calculation of the filing fees of the above application, please amend the application as follows:

IN THE CLAIMS:

Please amend the following claims as follows:

7. (Amended) The production method according to claim 1,  
wherein the oxy anion compound has no functional group other than an oxy anion group.

8. (Amended) The production method according to claim 1,  
wherein the oxy anion compound has a group represented by the general formula 1:



in the formula,  $R^1$  represents an organic group which may optionally contain one or more ether or ester linkages, and  $M^+$  represents an alkali metal ion or a quaternary ammonium ion.

10. (Amended) The production method according to claim 8,  
wherein, in the general formula 1 or 2,  $R^1$  or  $R^2$  is a univalent or bivalent organic group.

11. (Amended) The production method according to claim 9,  
wherein, in the general formula 2,  $R^2$  is an aromatic group.

12. (Amended) The production method according to claim 8,  
wherein, in the general formula 1,  $M^+$  is a potassium ion.

13. (Amended) The production method according to claim 1,  
wherein the oxy anion compound comprises at least one salt selected from the group  
consisting of alkoxide salts, phenoxide salts and carboxylate salts, and the counter ion thereto is an  
alkali metal ion or a quaternary ammonium ion.

16. (Amended) The production method according to claim 1,  
wherein the vinyl polymer (I) is produced by atom transfer radical polymerization.

19. (Amended) The production method according to claim 1,  
wherein a main chain of the vinyl polymer (I) is a (meth) acrylic polymer.

21. (Amended) The production method according to claim 1,

wherein the main chain of the vinyl polymer (I) is a styrenic polymer.

22. (Amended) The production method according to claim 1,

wherein a ratio ( $M_w/M_n$ ) between weight average molecular weight ( $M_w$ ) and number average molecular weight ( $M_n$ ) of the vinyl polymer (I) is less than 1.8 as determined by gel permeation chromatography.

23. (Amended) The production method according to claim 1,

wherein the number average molecular weight of the vinyl polymer (I) is within the range of 500 to 100,000.

24. (Amended) A vinyl polymer

which is producible by the production method according to claim 1.

REMARKS

The above amendment is believed to place the claims in proper condition for examination.  
Early and favorable action is awaited.

Attached hereto is a marked-up version of the changes made to the claims by the current amendment. The attached page is captioned "Version with markings to show changes made."

In the event there are any additional fees required, please charge our Deposit Account No.  
01-2340.

Respectfully submitted,

ARMSTRONG, WESTERMAN, HATTORI,  
McLELAND & NAUGHTON, LLP



Stephen G. Adrian  
Reg. No. 32,878

Atty. Docket No. 011300  
Suite 1000  
1725 K Street, N.W.  
Washington, D.C. 20006  
Tel: (202) 659-2930  
SGA/yap

VERSION WITH MARKINGS TO SHOW CHANGES MADE

The following claims have been amended as follows:

7. (Amended) The production method according to ~~any of Claims 1 to 6~~ claim 1, wherein the oxy anion compound has no functional group other than an oxy anion group.

8. (Amended) The production method according to ~~any of Claims 1 to 7~~ claim 1, wherein the oxy anion compound has a group represented by the general formula 1:



in the formula,  $R^1$  represents an organic group which may optionally contain one or more ether or ester linkages, and  $M^+$  represents an alkali metal ion or a quaternary ammonium ion.

10. (Amended) The production method according to claim 8 ~~or 9~~, wherein, in the general formula 1 or 2,  $R^1$  or  $R^2$  is a univalent or bivalent organic group.

11. (Amended) The production method according to claim 9 ~~or 10~~, wherein, in the general formula 2,  $R^2$  is an aromatic group.

12. (Amended) The production method according to ~~any of Claims 8 to 11~~ claim 8, wherein, in the general formula 1,  $M^+$  is a potassium ion.

13. (Amended) The production method according to ~~any of Claims 1 to 7~~ claim 1,



wherein the oxy anion compound comprises at least one salt selected from the group consisting of alkoxide salts, phenoxide salts and carboxylate salts, and the counter ion thereto is an alkali metal ion or a quaternary ammonium ion.

16. (Amended) The production method according to ~~any of Claims 1 to 15~~ claim 1, wherein the vinyl polymer (I) is produced by atom transfer radical polymerization.

19. (Amended) The production method according to ~~any of Claims 1 to 18~~ claim 1, wherein a main chain of the vinyl polymer (I) is a (meth) acrylic polymer.

21. (Amended) The production method according to ~~any of Claims 1 to 18~~ claim 1, wherein the main chain of the vinyl polymer (I) is a styrenic polymer.

22. (Amended) The production method according to ~~any of Claims 1 to 21~~ claim 1, wherein a ratio ( $M_w/M_n$ ) between weight average molecular weight ( $M_w$ ) and number average molecular weight ( $M_n$ ) of the vinyl polymer (I) is less than 1.8 as determined by gel permeation chromatography.

23. (Amended) The production method according to ~~any of Claims 1 to 22~~ claim 1, wherein the number average molecular weight of the vinyl polymer (I) is within the range of 500 to 100,000.

24. (Amended) A vinyl polymer which is producible by the production method according to ~~any of Claims 1 to 23~~ claim 1.

## IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re the Application of: **Yoshiki NAKAGAWA et al.**Serial Number: **09/926,254**

Group Art Unit: Unassigned

Filed: **October 1, 2001**

Examiner: Unassigned

For: **METHOD OF TREATING POLYMER****PRELIMINARY AMENDMENT**Commissioner for Patents  
Washington, D.C. 20231

Date: February 1, 2002

Sir:

Prior to examination on the merits, please amend the above-identified application as follows:

**IN THE SPECIFICATION:****Please amend the specification as follows:**

**Please replace the paragraph beginning at page 29, line 27, with the following rewritten paragraph:**



A more specific production method of the above oxy anion compound is now further described. When, for example, o-, m- or p-  $\text{CH}_3\text{-C}_6\text{H}_4\text{-OH}$  is used as the precursor, the base, for example potassium tert-butoxide, is charged into a reaction vessel under an inert gas atmosphere and suspended and dispersed in a solvent such as dimethylacetamide. The above methylphenol is added in an equimolar amount to this dispersion and the reaction is allowed to proceed at room temperature to  $70^\circ\text{C}$  for 30 minutes to 1 hour, whereupon the oxy anion compound resulting from substitution of potassium for the acidic proton is obtained.

09/926,254


Please replace the paragraph beginning at page 34, line 25, with the following

**rewritten paragraph:**

The (B) component, namely hydrosilyl group-containing compound, is not particularly restricted but may be any of various ones. Thus, usable are linear polysiloxanes represented by the following general formula (9) or (10):





in the formula,  $R^{17}$  and  $R^{18}$  are the same or different and each represents an alkyl group containing 1 to 6 carbon atoms or a phenyl group,  $R^{19}$  represents an alkyl group containing 1 to 10 carbon atoms or an aralkyl group containing 7 to 10 carbon atoms, a represents an integer of 0 to 100, b represents an integer of 2 to 100 and c represents an integer of 0 to 100; and cyclic polysiloxanes represented by the following general formula (11):





in the formula,  $R^{17}$  and  $R^{18}$  each represents an alkyl group containing 1 to 6 carbon atoms or a phenyl group,  $R^{19}$  represents an alkyl group containing 1 to 10 carbon atoms or an aralkyl group containing 7 to 10 carbon atoms, d represents an integer of 0 to 8, e represents an integer of 2 to 10, f represents an integer of 0 to 8 and d, e and f satisfy the relation  $3 \leq d + e + f \leq 10$ .

Please replace the paragraph beginning at page 35, line 14, with the following rewritten paragraph:

These may be used singly or two or more of them may be used in admixture. Among these polysiloxanes, phenyl group-containing polysiloxanes are preferred in view of their compatibility with vinyl polymers. As examples of such compounds, there may be mentioned linear siloxanes represented by the general formula (12) or (13) given below and cyclic polysiloxanes represented by the general formula (14) or (15) given below:



in the formula,  $\text{R}^{20}$  represents a hydrogen or a methyl group, g represents an integer of 2 to 100, h represents an integer of 0 to 100 and  $\text{C}_6\text{H}_5$  is a phenyl group;



in the formula,  $R^{20}$  represents a hydrogen or a methyl group,  $i$  represents an integer of 2 to 10,  $j$  represents an integer of 0 to 8,  $i$  and  $j$  satisfy the relation  $3 \leq i + j \leq 10$  and  $C_6H_5$  is a phenyl group.

**REMARKS**

The above-amendments are made to place the application in better condition for examination.

Prompt and favorable action on the merits is earnestly solicited.


Attached hereto is a marked-up version of the changes made to the specification as

“Version with markings to show changes made.”

In the event any fees are due with respect to this paper, please charge our Deposit Account No. **01-2340**.

Respectfully submitted,

ARMSTRONG, WESTERMAN & HATTORI, LLP



Stephen G. Adrian  
Reg. No. 32,878

Attorney Docket No. **011300**  
Suite 1000, 1725 K Street  
Washington, D.C. 20006  
Tel: (202) 659-2930  
Fax: (202) 887-0357  
SGA/arf

**IN THE SPECIFICATION:**



**Please amend the specification as follows:**

**Paragraph beginning at page 29, line 27 has been amended as follows:**

A more specific production method of the above oxy anion compound is now further described. When, for example, o-, ~~m- or p-~~ [or m-] CH<sub>3</sub>-C<sub>6</sub>H<sub>4</sub>-OH is used as the precursor, the base, for example potassium tert-butoxide, is charged into a reaction vessel under an inert gas atmosphere and suspended and dispersed in a solvent such as dimethylacetamide. The above methylphenol is added in an equimolar amount to this dispersion and the reaction is allowed to proceed at room temperature to 70°C for 30 minutes to 1 hour, whereupon the oxy anion compound resulting from substitution of potassium for the acidic proton is obtained.


**Paragraph beginning at page 34, line 25 has been amended as follows:**

The (B) component, namely hydrosilyl group-containing compound, is not particularly restricted but may be any of various ones. Thus, usable are linear polysiloxanes represented by the following general formula (9) or (10):



in the formula, R<sup>17</sup> and R<sup>18</sup> are the same or different and each represents an alkyl group containing 1 to 6 carbon atoms or a phenyl group, R<sup>19</sup> represents an alkyl group containing 1 to 10 carbon atoms or an aralkyl group containing 7 to 10 carbon atoms, a represents an integer of 0



to 100, b represents an integer of 2 to 100 and c represents an integer of 0 to 100; and cyclic polysiloxanes represented by the following general formula (11):



in the formula, R<sup>17</sup> and R<sup>18</sup> each represents an alkyl group containing 1 to 6 carbon atoms or a phenyl group, R<sup>19</sup> represents an alkyl group containing 1 to 10 carbon atoms or an aralkyl group containing 7 to 10 carbon atoms, d represents an integer of 0 to 8, e represents an integer of 2 to 10, f represents an integer of 0 to 8 and d, e and f satisfy the relation 3 ≤ d + e + f ≤ 10.

**Paragraph beginning at page 35, line 14 has been amended as follows:**


These may be used singly or two or more of them may be used in admixture. Among these polysiloxanes, phenyl group-containing polysiloxanes are preferred in view of their compatibility with vinyl polymers. As examples of such compounds, there may be mentioned linear siloxanes represented by the general formula (12) or (13) given below and cyclic polysiloxanes represented by the general formula (14) or (15) given below:






VERSION WITH MARKINGS TO SHOW CHANGES MADE (09/926,254)

in the formula,  $R^{20}$  represents a hydrogen or a methyl group,  $g$  represents an integer of 2 to 100,  $h$  represents an integer of 0 to 100 and  $C_6H_5$  is a phenyl group;



[(19)] (14)



[(20)] (15)

in the formula,  $R^{20}$  represents a hydrogen or a methyl group,  $i$  represents an integer of 2 to 10,  $j$  represents an integer of 0 to 8,  $i$  and  $j$  satisfy the relation  $3 \leq i + j \leq 10$  and  $C_6H_5$  is a phenyl group.

## SPECIFICATION

METHOD OF TREATING POLYMER

5

## TECHNICAL FIELD

The present invention relates to a method of treating the terminal halogen group of a vinyl polymer.

## BACKGROUND ART

10

It is known that polymers having a main chain terminated in an alkenyl group as a crosslinkable functional group, when subjected to the reaction with a hydrosilyl group-containing compound as a curing agent or to photoreaction, is crosslinked and gives curing products excellent in heat resistance, durability and other properties. As examples of the main chain skeleton of such polymer having an alkenyl group-terminated main chain, there may be mentioned, among others, polyether polymers such as polyethylene oxide; hydrocarbon polymers such as polyisobutylene, polybutadiene, polyisoprene and polychloroprene, and hydrogenated derivatives thereof; and polyester polymers such as polyethylene terephthalate, polybutylene terephthalate and polycaprolactone. These are used in various fields of application according to the main chain skeleton and the mode of crosslinking.

25

While these polymers are obtained by ionic polymerization or polycondensation, vinyl polymers obtained by radical polymerization and having a crosslinkable functional group-terminated main chain have scarcely been put to practical use. Among vinyl polymers, (meth)acrylic polymers have such characteristic features as high weathering resistance and transparency that the above-mentioned polyether polymers or polyester polymers cannot have. Thus, for example, (meth)acrylic polymers having an alkenyl group on side chains, not at either main chain terminus, are utilized in high weathering resistance coatings.

35

In contrast to such vinyl polymers having an alkenyl group on side chains, vinyl polymers having an alkenyl group-terminated main chain can give curing products with good curing characteristics. Therefore, a large number of researchers have endeavored to develop a simple and easy method of producing them. It is not easy, however, to produce them on an industrial scale. Japanese Kokai Publication Hei-04-132706 discloses a method of introducing a hydroxyl group by converting a halogen group at a polymer terminus. In crosslinking a polymer having a hydroxyl group-terminated main chain, however, it is necessary in many instances to use an isocyanate, which may pose a toxicity and/or stability problem. Hence, an alkenyl group or a crosslinkable silyl group is preferred as the crosslinkable terminal group.

Japanese Kokai Publication Hei-01-247403 discloses a method of synthesizing vinyl polymers having an alkenyl group at each of both termini which comprises using an alkenyl group-containing disulfide as a chain transfer agent. Further, Japanese Kokai Publication Hei-06-211922 discloses a method of synthesizing vinyl polymers having an alkenyl group at each of both termini which comprises synthesizing a vinyl polymer having a hydroxyl group at each of both termini using a hydroxyl-containing disulfide as a chain transfer agent and further introducing the alkenyl group into each terminus by utilizing the reactivity of the hydroxyl group. These methods, however, require the use of the chain transfer agent in large amounts for introducing the alkenyl group into both termini without fail, producing problems from the production process viewpoint. In addition, these methods employ the conventional radical polymerization, hence it is very difficult to control the molecular weight and molecular weight distribution (ratio between weight average molecular weight and number average molecular weight) of the polymer to be obtained.

Recently, the present inventors have succeeded in introducing various functional groups such as alkenyl, crosslinkable silyl and hydroxyl groups terminally into vinyl

polymers by utilizing the technology of controlled radical polymerization, preferably living radical polymerization, more preferably atom transfer radical polymerization (see, for example, Japanese Kokai Publication Hei-11-080249, Japanese Kokai Publication Hei-11-080250, Japanese Kokai Publication Hei-11-005815, Japanese Kokai Publication Hei-11-116617, Japanese Kokai Publication Hei-11-116606, Japanese Kokai Publication Hei-11-080571, Japanese Kokai Publication Hei-11-080570, Japanese Kokai Publication Hei-11-130931, Japanese Kokai Publication Hei-11-100433, Japanese Kokai Publication Hei-11-116763, Japanese Kokai Publication Hei-09-272714 and Japanese Kokai Publication Hei-09-272715).

On the other hand, in cases where the polymer contains a halogen, the halogen may cause various problems in using this polymer in various fields of application. For example, it may corrode metals in contact therewith, or reduce the storage stability of curable compositions comprising the polymer. In cases where the polymer is a product obtained by atom transfer radical polymerization, for instance, the polymer terminus or termini have a halogen introduced therein and, therefore, such problems as mentioned above become more serious.

Meanwhile, WO 99/54365 discloses a method of eliminating a halogen group from polymer terminus as halogen-containing compound by utilizing addition and elimination reactions of a specific double bond-containing compound. By this method, however, an acidic compound such as a hydrogen halide will be produced. In addition, unexpected side reactions such as crosslinking reactions may possibly proceed.

In view of the above-mentioned state of the art, it is an object of the present invention to reduce the halogen content of a halogen-containing polymer and thus provide a polymer and a curable composition, without producing such problems as corrosion of metals in contact with the same or reduction in storage stability.

## DISCLOSURE OF INVENTION

The present invention relates to a production method of a vinyl polymer with a reduced halogen content comprising treating a halogen group-containing vinyl polymer (I) with an oxy anion compound to thereby reduce the halogen content of the polymer.

It is preferred that the vinyl polymer (I) has a halogen group at a molecular chain terminus.


It is also preferred that the vinyl polymer (I) has a functional group other than a halogen group in a terminal structure thereof in addition to the above-mentioned halogen group.

It is preferred that the vinyl polymer (I), but not limited to, has at least one group selected from the group consisting of alkenyl, silyl, epoxy, hydroxyl and amino groups in the terminal structure thereof.


When the vinyl polymer (I) has an alkenyl group in a terminal structure thereof, after the elimination of the halogen group by means of an oxy anion compound, it is preferred that a crosslinkable silyl group-containing hydrosilane compound is caused to be added to the alkenyl group.

The oxy anion compound is not limited to any particular species but is preferably one having no functional group other than an oxy anion group.

The oxy anion compound is preferably one having a group represented by the general formula 1, it is more preferred that in the general formula 1,  $R^1$  is an organic group represented by the general formula 2.



In the formula,  $R^1$  represents an organic group, which may optionally contain one or more ether or ester linkages, and  $M^+$  represents an alkali metal ion or a quaternary ammonium ion.



In the formula,  $R^2$  represents an organic group, which may optionally contain one or more ether or ester linkages.

In the general formula 1 or 2,  $R^1$  or  $R^2$  is preferably a univalent or bivalent organic group.

In the general formula 2,  $R^2$  is preferably an aromatic group.

- 5 In the general formula 1,  $M^+$  is preferably a potassium ion.

The oxy anion compound preferably comprises at least one salt selected from the group consisting of alkoxide salts, phenoxide salts and carboxylate salts, and the counter ion thereto is preferably an alkali metal ion or a quaternary ammonium ion.

A univalent or bivalent carboxylate salt is more preferred among others, and more preferred is the one derived from any of benzoic acids or an acetic acid.

- 15 The vinyl polymer (I) is preferably one produced by atom transfer radical polymerization.

The terminal halogen group of the vinyl polymer (I) is not particularly restricted but may be one having a structure represented by the general formula 3.

- 20  $-C(R^3)(R^4)(X) \quad (3)$

In the formula,  $R^3$  and  $R^4$  are the same or different and each represents a hydrogen atom or a univalent organic group respectively derived from the group bound to the polymerizable carbon-carbon double bond group in the vinyl monomer constituting the above-mentioned polymer, and X represents a chlorine, bromine or iodine.

As the terminal halogen group of the vinyl polymer (I), in atom transfer radical polymerization, there may be mentioned a halogen group resulting from addition of an olefin compound having low polymerizability to a polymer terminus upon addition of the olefin compound during or at the end of the polymerization.

A main chain of the vinyl polymer (I) is preferably a (meth)acrylic polymer or a styrenic polymer, more preferably an acrylic polymer.

- 35 It is preferred a ratio ( $M_w/M_n$ ) between weight average

molecular weight (Mw) and number average molecular weight (Mn) of the vinyl polymer (I) is less than 1.8 as determined by gel permeation chromatography.

- 5 The number average molecular weight of the vinyl polymer (I) is preferably within the range of 500 to 100,000.

The present invention is also directed to a vinyl polymer with the halogen group eliminated therefrom by the method mentioned above.

- 10 The present invention is further directed to a curable composition which comprises the vinyl polymer having a crosslinkable silyl group in a terminal structure thereof as treated by the method mentioned above.

- The present invention is still further directed to a curable composition which comprises (A) the polymer having an alkenyl group in a terminal structure thereof as treated by the method mentioned above and (B) a hydrosilyl group-containing compound.

In the following, the present invention is described in detail.

- 20 The present invention is concerned with a production method of vinyl polymers which comprises treating a halogen group-terminated vinyl polymer (I) with an oxy anion compound to thereby reduce the halogen content of the polymer.

- 25 The oxy anion compound is not limited to a particular species but preferably has no functional group other than oxy anion group so that the physical properties of the vinyl polymer to be treated may not be influenced as far as possible upon treatment of the halogen group.

- 30 The oxy anion compound preferably has a group represented by the general formula 1, more preferably, in the general formula 1,  $R^1$  is a group represented by the general formula 2.



- In the formula,  $R^1$  represents an organic group, which may optionally contain one or more ether or ester linkages, and  $M^+$  represents an alkali metal ion or a quaternary ammonium ion.
- 35



In the formula,  $\text{R}^2$  represents a direct bond or an organic group, which may optionally contain one or more ether or ester linkages.

- Referring to the above general formula (1) or (2),  $\text{R}^1$  and  $\text{R}^2$  represent organic groups, which may optionally contain one or more ether or ester linkages. The organic groups may be univalent, bivalent, trivalent or tetravalent but is preferably univalent or bivalent.

- Preferably,  $\text{R}^1$  and  $\text{R}^2$  in the general formula (1) and (2) are respectively a univalent or bivalent hydrocarbon group containing 1 to 20 carbon atoms.

The univalent organic group specifically includes, but is not limited to, the following groups:

- $-(\text{CH}_2)_n-\text{CH}_3$ ,  $-\text{CH}(\text{CH}_3)-(\text{CH}_2)_n-\text{CH}_3$ ,  $-\text{CH}(\text{CH}_2\text{CH}_3)-(\text{CH}_2)_n-\text{CH}_3$ ,  
 15  $-\text{CH}(\text{CH}_2\text{CH}_3)_2$ ,  $-\text{C}(\text{CH}_3)_2-(\text{CH}_2)_n-\text{CH}_3$ ,  $-\text{C}(\text{CH}_3)(\text{CH}_2\text{CH}_3)-(\text{CH}_2)_n-\text{CH}_3$ ,  
 $-\text{C}_6\text{H}_5$ ,  $-\text{C}_6\text{H}_5(\text{CH}_3)$ ,  $-\text{C}_6\text{H}_5(\text{CH}_3)_2$ ,  $-(\text{CH}_2)_n-\text{C}_6\text{H}_5$ ,  $-(\text{CH}_2)_n-\text{C}_6\text{H}_5(\text{CH}_3)$ ,  
 $-(\text{CH}_2)_n-\text{C}_6\text{H}_5(\text{CH}_3)_2$   
 in the formula,  $n$  is an integer not less than 0 and the total number of carbon atoms in each group is not more than 20.  
 20 As typical examples of the bivalent organic group, there may be mentioned  $-(\text{CH}_2)_n-$ , in the formula,  $n$  represents an integer of 1 to 20;  $-\text{CH}(\text{CH}_3)-$ ,  $-\text{CH}(\text{CH}_2\text{CH}_3)-$ ,  $-\text{C}(\text{CH}_3)_2-$ ,  
 $-\text{C}(\text{CH}_3)(\text{CH}_2\text{CH}_3)-$ ,  $-\text{C}(\text{CH}_2\text{CH}_3)_2-$ ,  $-\text{CH}_2\text{CH}(\text{CH}_3)-$ ;  $-(\text{CH}_2)_n-\text{O}-$ , in each formula,  $n$  represents an integer of 1 to 20;  $-\text{CH}(\text{CH}_3)-\text{O}-$ ,  
 25  $-\text{CH}(\text{CH}_2\text{CH}_3)-\text{O}-$ ,  $-\text{C}(\text{CH}_3)_2-\text{O}-$ ,  $-\text{C}(\text{CH}_3)(\text{CH}_2\text{CH}_3)-\text{O}-$ ,  
 $-\text{C}(\text{CH}_2\text{CH}_3)_2-\text{O}-$ ;  $-(\text{CH}_2)_n-\text{O}-\text{CH}_2-$ , in each formula,  $n$  represents an integer of 1 to 19;  $-\text{CH}(\text{CH}_3)-\text{O}-\text{CH}_2-$ ,  $-\text{CH}(\text{CH}_2\text{CH}_3)-\text{O}-\text{CH}_2-$ ,  
 $-\text{C}(\text{CH}_3)_2-\text{O}-\text{CH}_2-$ ,  $-\text{C}(\text{CH}_3)(\text{CH}_2\text{CH}_3)-\text{O}-\text{CH}_2-$ ,  $-\text{C}(\text{CH}_2\text{CH}_3)_2-\text{O}-\text{CH}_2-$ ,  
 $-(\text{CH}_2)_2-\text{O}-\text{C}(\text{O})-$ ;  $-(\text{CH}_2)_n-\text{OC}(\text{O})-(\text{CH}_2)_m-$ , in each formula,  $m$  and  $n$   
 30 are the same or different, and represent an integer of 0 to 19 and satisfy  $0 \leq m + n \leq 19$ ;  $-(\text{CH}_2)_n-\text{C}(\text{O})\text{O}-(\text{CH}_2)_m-$ , in the formula,  $m$  and  $n$  are the same or different and represent an integer of 0 to 19, and satisfy  $0 \leq m + n \leq 19$ ;  $-\text{CH}_2-\text{C}(\text{O})\text{O}-(\text{CH}_2)_2-\text{O}-\text{CH}_2-$ ,  
 $-\text{CH}(\text{CH}_3)-\text{C}(\text{O})\text{O}-(\text{CH}_2)_2-\text{O}-\text{CH}_2-$ ,  $-\text{CH}(\text{CH}_2\text{CH}_3)-\text{C}(\text{O})\text{O}-(\text{CH}_2)_2-\text{O}-$ ,  
 35  $-\text{C}(\text{CH}_3)_2-\text{C}(\text{O})\text{O}-$ ,  $-\text{C}(\text{CH}_3)(\text{CH}_2\text{CH}_3)-\text{C}(\text{O})\text{O}-$ ,  $-\text{C}(\text{CH}_2\text{CH}_3)_2-\text{C}(\text{O})\text{O}-$  and



so forth.

In certain specific examples of the bivalent organic group, it may contain a benzene ring. Specific examples in this case are o-, m- or p-C<sub>6</sub>H<sub>4</sub>-, o-, m- or p-C<sub>6</sub>H<sub>4</sub>-CH<sub>2</sub>-, o-, m- or p-C<sub>6</sub>H<sub>4</sub>-O-,  
 5 o-, m- or p-C<sub>6</sub>H<sub>4</sub>-O-CH<sub>2</sub>-, o-, m- or p-C<sub>6</sub>H<sub>4</sub>-O-CH(CH<sub>3</sub>)-, o-, m- or p-C<sub>6</sub>H<sub>4</sub>-O-C(CH<sub>3</sub>)<sub>2</sub>-; o-, m- or p-C<sub>6</sub>H<sub>4</sub>-(CH<sub>2</sub>)<sub>n</sub>-, in each formula, n represents an integer of 0 to 14; o-, m- or p-C<sub>6</sub>H<sub>4</sub>-O-(CH<sub>2</sub>)<sub>n</sub>-, in each formula, n represents an integer of 0 to 14; o-, m- or p-CH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-, o-, m- or p-CH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-CH<sub>2</sub>-, o-, m- or p-CH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-O-,  
 10 o-, m- or p-CH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-O-CH<sub>2</sub>-, o-, m- or p-CH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-O-CH(CH<sub>3</sub>)-, o-, m- or p-CH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-O-C(CH<sub>3</sub>)<sub>2</sub>-; o-, m- or p-CH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-(CH<sub>2</sub>)<sub>n</sub>-, in each formula, n represents an integer of 0 to 13; o-, m- or p-CH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-O-(CH<sub>2</sub>)<sub>n</sub>-, in each formula, n represents an integer of 0 to 13; o-, m- or p-C<sub>6</sub>H<sub>4</sub>-C(O)O-, o-, m- or p-CH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-C(O)O-;  
 15 o-, m- or p-C(O)-C<sub>6</sub>H<sub>4</sub>-C(O)O-(CH<sub>2</sub>)<sub>n</sub>-, in each formula, n represents an integer of 0 to 12, and the like.

Referring to the above general formula 1, M<sup>+</sup> is a counter cation to the oxy anion and represents an alkali metal ion or a quaternary ammonium ion. The alkali metal ion includes a  
 20 lithium ion, a sodium ion and a potassium ion, among others, preferably is a sodium ion or a potassium ion, and more preferably a potassium ion. The quaternary ammonium ion includes a tetramethylammonium ion, a tetraethylammonium ion, a trimethylbenzylammonium ion, a trimethyldodecylammonium ion,  
 25 a tetrabutylammonium ion, a dimethylpiperidinium ion and so forth.

<Vinyl polymer (I)>

<Main chain of the polymer>

Various monomers can be used for constituting the main  
 30 chain of the vinyl polymer (I) of the present invention, without any particular restriction. Thus, examples are (meth)acrylic monomers such as (meth)acrylic acid, methyl (meth)acrylate, ethyl (meth)acrylate, n-propyl (meth)acrylate, isopropyl (meth)acrylate, n-butyl (meth)acrylate, isobutyl  
 35 (meth)acrylate, tert-butyl (meth)acrylate, n-pentyl

- (meth)acrylate, n-hexyl (meth)acrylate, cyclohexyl (meth)acrylate, n-heptyl (meth)acrylate, n-octyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, nonyl (meth)acrylate, decyl (meth)acrylate, dodecyl (meth)acrylate,
- 5 myristyl (meth)acrylate, palmityl (meth)acrylate, stearyl (meth)acrylate, eicosyl (meth)acrylate, phenyl (meth)acrylate, toluyl (meth)acrylate, benzyl (meth)acrylate, 2-methoxyethyl (meth)acrylate, 3-methoxybutyl (meth)acrylate, 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate, stearyl
- 10 (meth)acrylate, glycidyl (meth)acrylate, 2-aminoethyl (meth)acrylate,  $\gamma$ -(methacryloyloxypropyl)trimethoxysilane, (meth)acrylic acid-ethylene oxide adducts, trifluoromethylmethyl (meth)acrylate, 2-trifluoromethylethyl (meth)acrylate, 2-perfluoroethylethyl (meth)acrylate,
- 15 2-perfluoroethyl-2-perfluorobutylethyl (meth)acrylate, 2-perfluoroethyl (meth)acrylate, perfluoromethyl (meth)acrylate, diperfluoromethylmethyl (meth)acrylate, 2-perfluoromethyl-2-perfluoroethylmethyl (meth)acrylate, 2-perfluorohexylethyl (meth)acrylate, 2-perfluorodecylethyl
- 20 (meth)acrylate and 2-perfluorohexadecylethyl (meth)acrylate; styrenic monomers such as styrene, vinyltoluene,  $\alpha$ -methylstyrene, chlorostyrene and styrenesulfonic acid, and salts thereof; fluorine-containing vinyl monomers such as perfluoroethylene, perfluoropropylene and vinylidene fluoride;
- 25 silicon-containing vinyl monomers such as vinyltrimethoxysilane and vinyltriethoxysilane; maleic anhydride, maleic acid, maleic acid monoalkyl esters and dialkyl esters; fumaric acid, fumaric acid monoalkyl esters and dialkyl esters; maleimide monomers such as maleimide, methylmaleimide, ethylmaleimide, propylmaleimide, butylmaleimide,
- 30 hexylmaleimide, octylmaleimide, dodecylmaleimide, stearylmaleimide, phenylmaleimide and cyclohexylmaleimide; nitrile group-containing vinyl monomers such as acrylonitrile and methacrylonitrile; amide group-containing vinyl monomers
- 35 such as acrylamide and methacrylamine; vinyl esters such as vinyl

acetate, vinyl propionate, vinyl pivalate, vinyl benzoate and vinyl cinnamate; alkenes such as ethylene and propylene; conjugated dienes such as butadiene and isoprene; vinyl chloride, vinylidene chloride, allyl chloride, allyl alcohol and so forth.

- 5 These may be used singly or a plurality thereof may be copolymerized. Among them, styrenic monomers and (meth)acrylic monomers are preferred from the viewpoint of physical properties of products. More preferred are acrylic acid ester monomers and methacrylic acid ester monomers, among which butyl acrylate
- 10 is further more preferred. In the practice of the invention, such preferred monomers may be copolymerized with another monomer or other monomers and, in that case, the preferred monomers preferably account for 40% by weight.

<Molecular weight and molecular weight distribution>

- 15 The vinyl polymer of the invention preferably has a molecular weight distribution, namely the ratio ( $M_w/M_n$ ) between weight average molecular weight ( $M_w$ ) and number average molecular weight ( $M_n$ ), of less than 1.8, more preferably not more than 1.7, still more preferably not more than 1.6, in particular not
- 20 more than 1.5, still further preferably not more than 1.4, most preferably not more than 1.3, as determined by gel permeation chromatography. In the practice of the invention, GPC measurements are generally carried out using polystyrene gel columns or the like, together with chloroform or tetrahydrofuran,
- 25 for instance, as a mobile phase. The molecular weight values are determined on the polystyrene equivalent basis.

- The number average molecular weight of the vinyl polymer (I) of the present invention is not limited to any particular range but preferably is within the range of 500 to 100,000, more
- 30 preferably 3,000 to 40,000. If the molecular weight is below 500, the characteristics intrinsic in vinyl polymers will hardly be manifested and, if it is above 100,000, polymer handling becomes difficult.

<Method of polymerization>

- 35 A production method of halogen group-terminated vinyl

polymers according to the present invention is not particularly restricted.

- 5 In the practice of the present invention, the polymer main chain is preferably produced by living radical polymerization or radical polymerization using a chain transfer agent, and the former is particularly preferred, although vinyl polymers are generally produced by anionic polymerization or radical polymerization.

- 10 The radical polymerization methods, which may be used in synthesizing the vinyl polymer (I) of the invention, can be classified into "ordinary radical polymerization methods" comprising copolymerizing a monomer having a specific functional group with a vinyl monomer using an azo compound or peroxide as a polymerization initiator and "controlled radical
- 15 polymerization methods" by which a specific functional group can be introduced at a controlled site, for example at a terminus.

- Although the "ordinary radical polymerization methods" are simple and easy, a specific functional group-containing monomer is introduced in a polymer only at random by these methods
- 20 and, therefore, for obtaining a highly functionalized polymer, it is necessary to use a large amount of that monomer. If, conversely, that monomer is used in a small amount, there arises the problem that the proportion of polymer molecules without having that specific functional group introduced therein
- 25 increases. A further problem is that the methods consist in free radical polymerization, polymers wide in molecular weight distribution and high in viscosity can only be obtained.

- The "controlled radical polymerization methods" can be further classified into "chain transfer agent methods" by which
- 30 functional group-terminated vinyl polymers can be obtained by carrying out the polymerization using a chain transfer agent containing a specific functional group and "living radical polymerization methods" by which a growing polymer terminus can grow without undergoing any termination or like reaction and
- 35 which thus can give polymers having a molecular weight

approximately as designed.

The "chain transfer agent methods" can give polymers with a high functionalization percentage but require the use of a fairly large amount, relative to the initiator, of a chain transfer agent having a specific functional group. Thus, there arise problems from an economic viewpoint, inclusive of problems with treatment. Like the above-mentioned "ordinary radical polymerization methods", they consist in free radical polymerization, hence there is the problem that only those polymers which are wide in molecular weight distribution and high in viscosity is obtainable.

Unlike these polymerization methods, the "living radical polymerization methods" can give polymers narrow in molecular weight distribution (about 1.1 to 1.5 in terms of  $M_w/M_n$ ) and allow the molecular weight to be arbitrarily controlled by varying the charge amount ratio between a monomer and a initiator while termination reactions hardly occur in spite of the fact that they consist in that radical polymerization which is high in rate of polymerization and readily allows the termination reaction due to radical-to-radical coupling to occur, hence is thought to be difficult to control.

Thus, the "living radical polymerization methods" can give polymers narrow in molecular weight distribution and low in viscosity and, in addition, make it possible to introduce a monomer having a specific functional group into polymers at substantially arbitrary sites as desired, hence is preferred as a production method of such specific functional group-containing vinyl polymers.

Although the term "living polymerization", in its narrower sense, denotes that mode of polymerization in which molecular chains grow while a terminus thereof always remain active, the term generally includes the pseudo living polymerization in which molecular chains grow while terminally inactivated species and terminally active species are in equilibrium. The latter definition applies to the present invention.

The "living radical polymerization methods" have been actively investigated in recent years by various groups of researchers. As examples thereof, there may be mentioned the method using a cobalt-porphyrin complex as reported in the  
5 Journal of the American Chemical Society, 1994, vol. 116, page 7943 ff, the method using a radical capping agent such as a nitroxide compound as reported in Macromolecules, 1994, vol. 27, pages 7228 ff, and the "atom transfer radical polymerization" (ATRP) in which an organic halide is used as an initiator and  
10 a transition metal complex as a catalyst.

Among the "living radical polymerization methods", the technique of "atom transfer radical polymerization" which comprises polymerizing a vinyl monomer using an organic halide or halosulfonyl compound as an initiator and a transition metal  
15 complex as a catalyst is more suited for use as a production method of vinyl polymers having a specific functional group since it gives polymers terminated in a halogen or the like, which is relatively advantageous to functional group conversion reactions, and is high in degree of freedom in initiator or  
20 catalyst designing while it has the above-mentioned characteristics of "living radical polymerization". This technique of "atom transfer radical polymerization" is described, for example, in Matyjaszewski et al., Journal of the American Chemical Society, 1995, vol. 117, pages 5614 ff; Macromolecules,  
25 1995, vol. 28, pages 7901 ff; Science, 1996, vol. 272, pages 866 ff; WO 96/30421, WO 97/18247, WO 98/01480, WO 98/40415; and Sawamoto et al., Macromolecules, 1995, vol. 28, pages 1721 ff.

Although any of those methods mentioned above may be used in the practice of the present invention without any particular  
30 restriction, the technique of controlled radical polymerization is basically utilized and, from the ease of control viewpoint, the technique of living radical polymerization is preferred and, in particular, when the atom transfer radical polymerization, which basically allows a halogen group to remain at a growing  
35 terminus, as mentioned later herein, is used, the effects of

the present invention are efficiently produced.

First, the polymerization technique using a chain transfer agent, one of the controlled radical polymerization methods, is explained. The technique of radical polymerization using a chain transfer agent (telomer) for obtaining vinyl polymers having a terminal structure suited for the purpose of the present invention includes, but is not particularly restricted to, the following two modifications.

One method uses a halogenated hydrocarbon as a chain transfer agent to obtain halogen-terminated polymers, as disclosed in Japanese Kokai Publication Hei-04-132706 and the other uses a hydroxyl group-containing mercaptan or a hydroxyl group-containing polysulfide as a chain transfer agent to obtain hydroxyl-terminated polymers, as disclosed in Japanese Kokai Publication Sho-61-271306, Japanese Patent 2594402 and Japanese Kokai Publication Sho-54-47782.

The living radical polymerization is now described.

Among them, the method which uses a radical capping agent such as a nitroxide compound is first described. In this method of polymerization, a nitroxyl free radical ( $=N-O\cdot$ ), which is generally stable, is used as a radical capping agent. Such compound is not particularly restricted but preferably is a 2,2,6,6-substituted-1-piperidinyloxy radical, a 2,2,5,5-substituted-1-pyrrolidinyloxy radical or a cyclic hydroxy amine-derived nitroxyl free radical. Suitable substituents are alkyl groups containing not more than 4 carbon atoms, such as methyl and ethyl groups. The nitroxyl free radical compound specifically includes, but is not limited to, 2,2,6,6-tetramethyl-1-piperidinyloxy radical (TEMPO), 2,2,6,6-tetraethyl-1-piperidinyloxy radical, 2,2,6,6-tetramethyl-4-oxo-1-piperidinyloxy radical, 2,2,5,5-tetramethyl-1-pyrrolidinyloxy radical, 1,1,3,3-tetramethyl-2-isindolinyloxy radical, N,N-di-tert-butylaminoxy radical and the like. Stable free radicals such as galvinoxyl free radical may be used in lieu


of the nitroxy free radicals.

The radical capping agent mentioned above is used in combination with a radical generator. It is considered that the reaction product from the radical capping agent and the radical generator serves as a polymerization initiator to cause the polymerization of an addition-polymerizable monomer to proceed. The mixing ratio therebetween is not particularly restricted but suitably is 0.1 to 10 moles of radical initiator per mole of radical capping agent.

While various compounds can be used as the radical generator, peroxides capable of generating radicals under polymerization temperature conditions are preferred. Such peroxides include, but are not limited to, diacyl peroxides such as benzoyl peroxide and lauroyl peroxide, dialkyl peroxides such as dicumyl peroxide and di-tert-butyl peroxide, peroxy carbonates such as diisopropyl peroxydicarbonate and bis(4-tert-butylcyclohexyl) peroxydicarbonate, and alkyl peresters such as tert-butyl peroxyoctoate and tert-butyl peroxybenzoate. In particular, benzoyl peroxide is preferred. Further, radical generators, for example radical-generating azo compounds such as azobisisobutyronitrile may also be used in lieu of the peroxides.

Alkoxyamine compounds such as illustrated below may be used as initiators instead of combinedly using a radical capping agent and a radical generator, as reported in *Macromolecules*, 1995, vol. 28, pages 2993 ff.





In cases where an alkoxyamine compound is used as an initiator, the use of one having a functional group such as a hydroxyl group, as illustrated above, leads to the formation of a functional group-terminated polymer.


The polymerization conditions, such as monomer, solvent and polymerization temperature, to be used in the polymerization using a radical capping agent such as the nitroxide compound mentioned above are not restricted but may be the same as in the atom transfer radical polymerization mentioned below.

Next, the atom transfer radical polymerization method, which is a more preferred mode of living radical polymerization in the practice of the present invention, is described.

In this atom transfer radical polymerization, an organic halide, in particular an organic halide having a highly reactive carbon-halogen bond (e.g. a carbonyl compound having a halogen at the  $\alpha$ -position or a compound having a halogen at the benzyl position) or a halosulfonyl compound is used as an initiator.

Thus, a halogen group generally occurs at the terminus of atom transfer radical polymerization and, therefore, the method of the present invention produces very good effects.

Specific examples of the above initiator are:



in the above chemical formulas,  $\text{C}_6\text{H}_5$  represents a phenyl group

and X is a chlorine, bromine or iodine;

$R^5-C(H)(X)-CO_2R^6$ ,  $R^5-C(CH_3)(X)-CO_2R^6$ ,  $R^5-C(H)(X)-C(O)R^6$ ,  
 $R^5-C(CH_3)(X)-C(O)R^6$ ,

in each formula,  $R^5$  and  $R^6$  each is a hydrogen atom or an alkyl group containing 1 to 20 carbon atoms, an aryl group or an aralkyl group and X is a chlorine, bromine or iodine;

$R^5-C_6H_4-SO_2X$

in the above formula,  $R^5$  is a hydrogen atom or an alkyl group containing 1 to 20 carbon atoms, an aryl group or an aralkyl group and X is a chlorine, bromine or iodine;

and the like.

An organic halide or halosulfonyl compound having a functional group other than a functional group initiating the polymerization may also be used as the atom transfer radical polymerization initiator. In such case, vinyl polymers having a functional group at one main chain terminus and a halogen group at the other main chain terminus are produced. As such functional group, there may be mentioned alkenyl, crosslinkable silyl, hydroxyl, epoxy, amino and amide groups, and so forth.

The alkenyl group-containing organic halide includes, but is not limited to, one having the structure represented by the general formula 4, for instance:




$R^8R^9C(X)-R^{10}-R^{11}-C(R^7)=CH_2$  (4)

in the formula,  $R^7$  is a hydrogen or a methyl group,  $R^8$  and  $R^9$  each represents a hydrogen or a univalent alkyl group containing 1 to 20 carbon atoms, an aryl group or an aralkyl group or  $R^8$  and  $R^9$  are bound to each other at their respective other ends,  $R^{10}$  is  $-C(O)O-$  (ester group),  $-C(O)-$  (keto group) or o-, m- or p-phenylene group,  $R^{11}$  is a direct bond or a bivalent organic group containing 1 to 20 carbon atoms, which may optionally contain one or more ether linkages, and X is a chlorine, bromine or iodine.





As specific examples of the substituents  $R^8$  and  $R^9$ , there may be mentioned a hydrogen, a methyl group, an ethyl group, a n-propyl group, an isopropyl group, a butyl group, a pentyl group, a hexyl group, etc.  $R^8$  and  $R^9$  may be bound together at

their respective other ends to form a cyclic skeleton.

As typical examples of the alkenyl group-containing organic halide, there may be mentioned:



in each of the above formulas, X is a chlorine, bromine or iodine and n is an integer of 0 to 20;



in each of the above formulas, X is a chlorine, bromine or iodine, n is an integer of 1 to 20 and m is an integer of 0 to 20;

o-, m- or p-XCH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-O-(CH<sub>2</sub>)<sub>n</sub>-CH=CH<sub>2</sub>, o-, m- or

p-CH<sub>3</sub>C(H)(X)-C<sub>6</sub>H<sub>4</sub>-O-(CH<sub>2</sub>)<sub>n</sub>-CH=CH<sub>2</sub>, o-, m- or

- 5 p-CH<sub>3</sub>CH<sub>2</sub>C(H)(X)-C<sub>6</sub>H<sub>4</sub>-O-(CH<sub>2</sub>)<sub>n</sub>-CH=CH<sub>2</sub>

in each of the above formulas, X is a chlorine, bromine or iodine and n is an integer of 0 to 20;

o-, m- or p-XCH<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-O-(CH<sub>2</sub>)<sub>n</sub>-O-(CH<sub>2</sub>)<sub>m</sub>-CH=CH<sub>2</sub>, o-, m- or


p-CH<sub>3</sub>C(H)(X)-C<sub>6</sub>H<sub>4</sub>-O-(CH<sub>2</sub>)<sub>n</sub>-O-(CH<sub>2</sub>)<sub>m</sub>-CH=CH<sub>2</sub>, o-, m- or

- 10 p-CH<sub>3</sub>CH<sub>2</sub>C(H)(X)-C<sub>6</sub>H<sub>4</sub>-O-(CH<sub>2</sub>)<sub>n</sub>-O-(CH<sub>2</sub>)<sub>m</sub>-CH=CH<sub>2</sub>

in each of the above formulas, X is a chlorine, bromine or iodine, n is an integer of 1 to 20 and m is an integer of 0 to 20.

As the alkenyl group-containing organic halide, there may further be mentioned compounds represented by the general formula



- 15 5:



in the formula, R<sup>7</sup>, R<sup>8</sup>, R<sup>9</sup>, R<sup>11</sup> and X are as defined above and R<sup>12</sup> represents a direct bond, -C(O)O- (ester group), -C(O)- (keto group) or o-, m- or p-phenylene group.

- 20 R<sup>10</sup> is a direct bond or a bivalent organic group containing 1 to 20 carbon atoms (which may optionally contain one or more ether linkages). When it is a direct bond, a vinyl group is bound to the carbon atom to which a halogen is bound, hence the compound is an allyl halide compound. In this case, the  
25 carbon-halogen bond is activated by the neighboring vinyl group and, therefore, it is not always necessary for R<sup>12</sup> to be a C(O)O or phenylene group but it may be a direct bond. In cases where R<sup>11</sup> is other than a direct bond, R<sup>12</sup> is preferably a C(O)O, C(O) or phenylene group so that the carbon-halogen bond may be  
30 activated.

Specific examples of the compound of the general formula 5 are:



- 35  $\text{CH}_2=\text{CHC}(\text{H})(\text{X})\text{CH}(\text{CH}_3)_2, \text{CH}_2=\text{CHC}(\text{H})(\text{X})\text{C}_6\text{H}_5, \text{CH}_2=\text{CHC}(\text{H})(\text{X})\text{CH}_2\text{C}_6\text{H}_5,$

$\text{CH}_2=\text{CHCH}_2\text{C}(\text{H})(\text{X})-\text{CO}_2\text{R}$ ,  $\text{CH}_2=\text{CH}(\text{CH}_2)_2\text{C}(\text{H})(\text{X})-\text{CO}_2\text{R}$ ,  
 $\text{CH}_2=\text{CH}(\text{CH}_2)_3\text{C}(\text{H})(\text{X})-\text{CO}_2\text{R}$ ,  $\text{CH}_2=\text{CH}(\text{CH}_2)_8\text{C}(\text{H})(\text{X})-\text{CO}_2\text{R}$ ,  
 $\text{CH}_2=\text{CHCH}_2\text{C}(\text{H})(\text{X})-\text{C}_6\text{H}_5$ ,  $\text{CH}_2=\text{CH}(\text{CH}_2)_2\text{C}(\text{H})(\text{X})-\text{C}_6\text{H}_5$ ,  
 $\text{CH}_2=\text{CH}(\text{CH}_2)_3\text{C}(\text{H})(\text{X})-\text{C}_6\text{H}_5$

- 5 in each of the above formulas, X is a chlorine, bromine or iodine and R is an alkyl group containing 1 to 20 carbon atoms, an aryl group or an aralkyl group.


Specific examples of the alkenyl group-containing halosulfonyl compound are:

- 10 o-, m- or p- $\text{CH}_2=\text{CH}-(\text{CH}_2)_n-\text{C}_6\text{H}_4-\text{SO}_2\text{X}$ , o-, m- or p- $\text{CH}_2=\text{CH}-(\text{CH}_2)_n-\text{O}-\text{C}_6\text{H}_4-\text{SO}_2\text{X}$

in each of the above formulas, X is a chlorine, bromine or iodine and n is an integer of 0 to 20, and the like.

The crosslinkable silyl group-containing organic halide


- 15 mentioned above is not particularly restricted but includes, for example, compounds having the structure represented by the general formula 6:










- 20 in the formula,  $\text{R}^7$ ,  $\text{R}^8$ ,  $\text{R}^9$ ,  $\text{R}^{10}$ ,  $\text{R}^{11}$  and X are as defined above,  $\text{R}^{13}$  and  $\text{R}^{14}$  each represents an alkyl group containing 1 to 20 carbon atoms, an aryl group or an aralkyl group or a triorganosiloxy group represented by  $(\text{R}')_3\text{SiO}-$  ( $\text{R}'$  is a univalent hydrocarbon group containing 1 to 20 carbon atoms and the three
- 25  $\text{R}'$  groups may be the same or different) and, when there are two or more  $\text{R}^{13}$  or  $\text{R}^{14}$  groups, they may be the same or different; Y represents a hydroxyl or hydrolysable group and, when there are two or more Y groups, they may be the same or different; a represents 0, 1, 2 or 3 and b represents 0, 1 or 2 and m is
- 30 an integer of 0 to 19 provided that the relation  $a + mb \geq 1$  should be satisfied.

Specific examples of the compound of the general formula 6 are:













- $\text{XCH}_2\text{C}(\text{O})\text{O}(\text{CH}_2)_n\text{Si}(\text{OCH}_3)_3$ ,  $\text{CH}_3\text{C}(\text{H})(\text{X})\text{C}(\text{O})\text{O}(\text{CH}_2)_n\text{Si}(\text{OCH}_3)_3$ ,  
 35  $(\text{CH}_3)_2\text{C}(\text{X})\text{C}(\text{O})\text{O}(\text{CH}_2)_n\text{Si}(\text{OCH}_3)_3$ ,  $\text{XCH}_2\text{C}(\text{O})\text{O}(\text{CH}_2)_n\text{Si}(\text{CH}_3)(\text{OCH}_3)_2$ ,



in each of the above formulas, X is a chlorine, bromine or iodine and n is an integer of 0 to 20;




in each of the above formulas, X is a chlorine, bromine or iodine, n is an integer of 1 to 20 and m is an integer of 0 to 20;



30 in each of the above formulas, X is a chlorine, bromine or iodine; and the like.

As the crosslinkable silyl group-containing organic halide, there may further be mentioned halides having the structure represented by the general formula 7:



(7)

in the formula,  $R^7$ ,  $R^8$ ,  $R^9$ ,  $R^{11}$ ,  $R^{12}$ ,  $R^{13}$ ,  $R^{14}$ ,  $a$ ,  $b$ ,  $m$ ,  $X$  and  $Y$  are as defined above.


Specific examples of such compound include

- 5  $(CH_3O)_3SiCH_2CH_2C(H)(X)C_6H_5$ ,  $(CH_3O)_2(CH_3)SiCH_2CH_2C(H)(X)C_6H_5$ ,  
 $(CH_3O)_3Si(CH_2)_2C(H)(X)-CO_2R$ ,  $(CH_3O)_2(CH_3)Si(CH_2)_2C(H)(X)-CO_2R$ ,  
 $(CH_3O)_3Si(CH_2)_3C(H)(X)-CO_2R$ ,  $(CH_3O)_2(CH_3)Si(CH_2)_3C(H)(X)-CO_2R$ ,  
 $(CH_3O)_3Si(CH_2)_4C(H)(X)-CO_2R$ ,  $(CH_3O)_2(CH_3)Si(CH_2)_4C(H)(X)-CO_2R$ ,  
 $(CH_3O)_3Si(CH_2)_5C(H)(X)-CO_2R$ ,  $(CH_3O)_2(CH_3)Si(CH_2)_5C(H)(X)-CO_2R$ ,  
 10  $(CH_3O)_3Si(CH_2)_3C(H)(X)-C_6H_5$ ,  $(CH_3O)_2(CH_3)Si(CH_2)_3C(H)(X)-C_6H_5$ ,  
 $(CH_3O)_3Si(CH_2)_4C(H)(X)-C_6H_5$ ,  $(CH_3O)_2(CH_3)Si(CH_2)_4C(H)(X)-C_6H_5$   
 in each of the above formulas,  $X$  is a chlorine, bromine or iodine  
 and  $R$  is an alkyl group containing 1 to 20 carbon atoms, an aryl  
 group or an aralkyl group; and the like.

- 15 The hydroxyl group-containing organic halide or  
 halosulfonyl compound is not particularly restricted but  
 includes such compounds as shown below:  
 $HO-(CH_2)_n-OC(O)C(H)(R)(X)$   
 in each of the above formulas,  $X$  is a chlorine, bromine or iodine,  
 20  $R$  is a hydrogen atom or an alkyl group containing 1 to 20 carbon  
 atoms, an aryl group or an aralkyl group and  $n$  is an integer  
 of 1 to 20.






- The amino group-containing organic halide or halosulfonyl  
 compound is not particularly restricted but includes such  
 25 compounds as shown below:  
 $H_2N-(CH_2)_n-OC(O)C(H)(R)(X)$   
 in each of the above formulas,  $X$  is a chlorine, bromine or iodine,  
 $R$  is a hydrogen atom or an alkyl group containing 1 to 20 carbon  
 atoms, an aryl group or an aralkyl group and  $n$  is an integer  
 30 of 1 to 20.

The epoxy group-containing organic halide or halosulfonyl  
 compound is not particularly restricted but includes such  
 compounds as shown below:





in each of the above formulas, X is a chlorine, bromine or iodine,  
 R is a hydrogen atom or an alkyl group containing 1 to 20 carbon  
 atoms, an aryl group or an aralkyl group and n is an integer  
 5 of 1 to 20.



An organic halide or halosulfonyl compound having two or  
 more initiation sites can also be used as the initiator. Specific  
 examples are:














5





5

and the like.

The vinyl monomer to be used in this polymerization is not particularly restricted but those specifically mentioned hereinabove all can be used satisfactorily.

10

The transition metal complex to be used as the polymerization catalyst is not particularly restricted but preferably is a metal complex containing, as the central metal,

an element of the group 7, 8, 9, 10 or 11 of the periodic table. As more preferred species, there may be mentioned complexes of zero-valence copper, univalent copper, bivalent ruthenium, bivalent iron or bivalent nickel. Among them, copper complexes  
 5 are preferred. Specific examples of the univalent copper compound are cuprous chloride, cuprous bromide, cuprous iodide, cuprouscyanide, cuprous oxide, cuprous perchlorate and the like. In cases where a copper compound is used, a ligand, for example 2,2'-bipyridyl or a derivative thereof, 1,10-phenanthroline or  
 10 a derivative thereof or a polyamine such as tetramethylethylenediamine, pentamethyldiethylenetriamine or hexamethyltris(2-aminoethyl)amine, is added for increasing the catalytic activity. The tris(triphenylphosphine) complex of bivalent ruthenium chloride ( $\text{RuCl}_2(\text{PPh}_3)_3$ ) is also suited for  
 15 use as the catalyst. In cases where a ruthenium compound is used as the catalyst, an aluminum alkoxide is added as an activator. Furthermore, the bis(triphenylphosphine) complex of bivalent iron ( $\text{FeCl}_2(\text{PPh}_3)_2$ ), the bis(triphenylphosphine) complex of bivalent nickel ( $\text{NiCl}_2(\text{PPh}_3)_2$ ) and the bis(tributylphosphine) complex of  
 20 bivalent nickel ( $\text{NiBr}_2(\text{PBu}_3)_2$ ) are also suitable as catalysts.

The polymerization can be carried out without using any solvent or in any of various solvents. As the solvent species, there may be mentioned hydrocarbon solvents such as benzene and toluene, ether solvents such as diethyl ether and tetrahydrofuran,  
 25 halogenated hydrocarbon solvents such as methylene chloride and chloroform, ketone solvents such as acetone, methyl ethyl ketone and methyl isobutyl ketone, alcohol solvents such as methanol, ethanol, propanol, isopropanol, n-butyl alcohol and tert-butyl alcohol, nitrile solvents such as acetonitrile, propionitrile  
 30 and benzonitrile, ester solvents such as ethyl acetate and butyl acetate, and carbonate solvents such as ethylene carbonate and propylene carbonate, and the like. These may be used singly or two or more of them may be used in admixture. The polymerization can be carried out within the temperature range  
 35 from room temperature to 200°C, preferably 50 to 150°C.

The terminus in atom transfer radical polymerization has a structure represented, for example, by the general formula 3:



5 in the formula,  $\text{R}^3$  and  $\text{R}^4$  are the same or different and each represents a hydrogen atom or univalent organic group derived from the group bound to the polymerizable carbon-carbon double bond group of the polymer-constituting vinyl monomer and X represents a chlorine, bromine or iodine.

10 As the terminal halogen group of the vinyl polymer (I), there may be mentioned a halogen group resulting from addition of an olefin compound having low polymerizability to a polymer terminus upon addition of that olefin compound during or at the endpoint of atom transfer radical polymerization.

15 Mainly for the purpose of terminally introducing a functional group, in atom transfer radical polymerization, in some cases, such an olefin compound having low polymerizability is added during or at the end of the polymerization to thereby cause that olefin to add to a polymer terminus.

20 The vinyl polymer (I) according to the present invention preferably has a terminal functional group other than the halogen group. More preferably, the vinyl polymer (I) of the invention has a crosslinkable terminal functional group [namely, a group to be involved in a following crosslinking reaction of the polymer  
25 obtained by the reaction of polymer (I) and oxy anion compound].

The vinyl polymer (I) is not particularly restricted but preferably has, at a terminus, at least one group selected from the group consisting of alkenyl, silyl, epoxy, hydroxyl and amino groups, more preferably an alkenyl group. When it has such a  
30 group, the present invention produces its effects more prominently in curable compositions in which that functional group is utilized, since terminal halogen groups may adversely affect the compositions in some cases.

The method of introducing such groups is not restricted  
35 but they are preferably introduced, in the above-mentioned atom

transfer radical polymerization, by adding an olefin compound having low polymerizability during or at the end point of the polymerization.

The olefin compound is not particularly restricted but includes 1,5-hexadiene, 1,7-octadiene, 1,9-decadiene; 10-undecenol, 5-hexenol, allyl alcohol; trimethoxysilylpropyl (meth)acrylate, methyldimethoxysilylpropyl (meth)acrylate and the like.

<Method of halogen group treatment>

According to the present invention, the terminal halogen of the vinyl polymer (I) is replaced by the oxy anion compound, whereby the terminal halogen group is eliminated. The treatment with the oxy anion compound only results in introduction of an ester or ether linkage, hence the problems caused by the halogen, for example metal corrosion and storage stability problems, can be solved without causing changes in intrinsic physical properties of the resulting polymer. Furthermore, since the treatment with the oxy anion compound can proceed under very mild conditions, that treatment is also advantageous in that the other functional group of the polymer will not be consumed or the polymer main chain will not be decomposed or the characteristics of the polymer will not be degraded. In the following, the method of effecting substitution with the oxy anion compound is described in detail.

As the oxy anion compound, those specifically mentioned above can be used.

The method of preparing the oxy anion compound is not restricted but may be prepared from an alcohol, such as methanol, ethanol or butanol; or a carboxylic acid, such as acetic acid or benzoic acid.

The oxy anion compound can be prepared by reacting the above precursor with a base. The base may be any of various ones. Examples thereof are sodium methoxide, potassium methoxide, lithium methoxide, sodium ethoxide, potassium ethoxide, lithium ethoxide, sodium tert-butoxide, potassium

tert-butoxide, sodium carbonate, potassium carbonate, lithium carbonate, sodium hydrogen carbonate, sodium hydroxide, potassium hydroxide, sodium hydride, potassium hydride, methylolithium, ethyllithium, n-butyllithium,

5 tert-butyllithium, lithium diisopropylamide, lithium hexamethyldisilazide; alkylamines such as trimethylamine, triethylamine and tributylamine; polyamines such as tetramethylethylenediamine and

10 pentamethyldiethylenetriamine; pyridine compounds such as pyridine and picoline; and the like. The base is used in an amount of 0.5 to 5 equivalents, preferably 0.8 to 1.2 equivalents, relative to the above precursor.

As the solvent which can be used in reacting the above precursor with the above base, there may be mentioned,

15 hydrocarbon solvents such as benzene and toluene; ether solvents such as diethyl ether and tetrahydrofuran; halogenated hydrocarbon solvents such as methylene chloride and chloroform; ketone solvents such as acetone, methyl ethyl ketone and methyl isobutyl ketone; alcohol solvents such as methanol, ethanol,

20 propanol, isopropanol, n-butyl alcohol and tert-butyl alcohol; nitrile solvents such as acetonitrile, propionitrile and benzonitrile; ester solvents such as ethyl acetate and butyl acetate; carbonate solvents such as ethylene carbonate and propylene carbonate; and amide solvents such as

25 dimethylformamide and dimethylacetamide. These may be used singly or two or more of them may be used in admixture.

A more specific production method of the above oxy anion compound is now further described. When, for example, o- or m- $\text{CH}_3\text{-C}_6\text{H}_4\text{-OH}$  is used as the precursor, the base, for example

30 potassium tert-butoxide, is charged into a reaction vessel under an inert gas atmosphere and suspended and dispersed in a solvent such as dimethylacetamide. The above methylphenol is added in an equimolar amount to this dispersion and the reaction is allowed to proceed at room temperature to 70°C for 30 minutes to 1 hour,

35 whereupon the oxy anion compound resulting from substitution

of potassium for the acidic proton is obtained.


Those oxy anion compounds in which  $M^+$  is a quaternary ammonium ion are obtainable by directly reacting the above precursor with an alkylamine or a pyridine compound. They can also be obtained by preparing an oxy anion compound in which  $M^+$  is an alkali metal ion by the above method and then reacting this with a quaternary ammonium halide. The quaternary ammonium halide is, for example, tetramethylammonium halide, tetraethylammonium halide, trimethylbenzylammonium halide, trimethyldodecylammonium halide or tetrabutylammonium halide.

In the practice of the present invention, the oxy anion compound is preferably one not having a functional group other than an oxy anion group. Further, the oxy anion compound is preferably free of any crosslinkable functional group [namely, a group to be involved in a following crosslinking reaction of the polymer obtained by reaction between the polymer (I) and the oxy anion compound].

By reacting the oxy anion compound prepared in the above manner with the vinyl polymer (I) obtained by the production method mentioned hereinabove, it is possible to eliminate the halogen from the polymer.

The reaction conditions in treating the halogen group with the oxy anion compound are not particularly restricted but a polar solvent is preferably used as a solvent. The solvent preferably includes, but is not limited to, amide solvents, more preferably N,N-dimethylacetamide (DMAC) and N,N-dimethylformamide (DMF). The reaction temperature is not restricted but the reaction can be carried out at room temperature to 200°C, preferably at 50°C to 150°C. The oxy anion compound is used in an amount of 1 to 5 equivalents, preferably 1 to 2 equivalents, more preferably 1 to 1.2 equivalents, relative to the halogen group.

As compared with the halogen group represented by the general formula 3:




(in the formula,  $R^3$  and  $R^4$  are the same or different and each represents a hydrogen atom or a univalent organic group derived from the group bound to the polymerizable carbon-carbon double bond group of the vinyl monomer and X represents a chlorine, bromine or iodine),

a halogen group resulting from addition of an olefin compound having low polymerizability to a polymer terminus upon addition of the olefin compound during or at the endpoint of atom transfer radical polymerization is lower in reactivity and severer conditions are required, for example a high temperature and the use of the oxy anion in excess. It is one of the characteristic features of the present invention that such a low reactivity halogen group can also be treated.

#### <Silylation>

Those polymers after halogen group treatment which have an alkenyl group can be converted to crosslinkable silyl group-containing vinyl polymers by causing a crosslinkable silyl group-containing hydrosilane compound to add thereto, and the storage stability of the resulting crosslinkable silyl group-containing vinyl polymers can be improved by the preceding halogen group treatment according to the present invention.

The crosslinkable silyl group-containing hydrosilane compound mentioned above is not particularly restricted but typically includes compounds represented by the general formula (8):



in the formula,  $R^{15}$  and  $R^{16}$  are the same or different and each represents an alkyl group containing 1 to 20 carbon atoms, an aryl group containing 6 to 20 carbon atoms, an aralkyl group containing 7 to 20 carbon atoms or a triorganosiloxy group represented by  $(R')_3SiO-$  (in which  $R'$  is a univalent hydrocarbon group containing 1 to 20 carbon atoms and the three  $R'$  groups may be the same or different) and, when there are two or more  $R^{15}$  or  $R^{16}$  groups, they may be the same or different; Y represents a hydroxyl group or a hydrolysable group and, when there are



two or more Y groups, they may be the same or different; a represents 0, 1, 2 or 3, b represents 0, 1 or 2 and m represents an integer of 0 to 19, provided that the relation  $a + mb \geq 1$  should be satisfied.

- 5 The above hydrolysable group represented by Y is not particularly restricted but may be any of those known in the art, specifically a hydrogen atom, halogen atoms, alkoxy, acyloxy, ketoximate, amino, amide, acid amide, aminoxy, mercapto, alkenyloxy groups, and the like. Among them, alkoxy groups are preferred in view of their mild hydrolyzability and ease of handling. One to three hydrolysable groups and/or hydroxyl groups represented by above Y may be bound to one silicon atom. Further,  $a + mb$ , namely the total number of hydrolysable groups and/or hydroxyl groups, is preferably within the range of 1 to 10
- 15 5. When two or more hydrolysable groups are bound to one silicon atom, they may be the same or different. The number of silicon atoms constituting the above hydrosilane compound may be 1 or 2 or more and, in the case of silicon atoms connected by siloxane bonding, that number may be up to about 20.

- 20 In the present description, the term "crosslinkable silyl group" indicates a silyl group where above Y group or groups bound to and which can form an  $-Si-O-Si-$  crosslink(s) by means of the hydroxyl group(s) or the hydroxyl group(s) formed upon hydrolysis of the hydrolysable group(s).

- 25 As specific examples of  $R^{15}$  and  $R^{16}$  in the above general formula (8), there may be mentioned, for example, alkyl groups such as methyl and ethyl; cycloalkyl groups such as cyclohexyl; aryl groups such as phenyl; aralkyl groups such as benzyl; and triorganosilyl groups represented by  $(R')_3SiO-$  in which  $R'$  is 30 methyl or phenyl, for instance.

- As typical examples of the hydrosilane compound represented by the above general formula (8), there may be mentioned  $HSiCl_3$ ,  $HSi(CH_3)Cl_2$ ,  $HSi(CH_3)_2Cl$ ,  $HSi(OCH_3)_3$ ,  $HSi(CH_3)(OCH_3)_2$ ,  $HSi(CH_3)_2OCH_3$ ,  $HSi(OC_2H_5)_3$ ,  $HSi(CH_3)(OC_2H_5)_2$ , 35  $HSi(CH_3)_2OC_2H_5$ ,  $HSi(OC_3H_7)_3$ ,  $HSi(C_2H_5)(OCH_3)_2$ ,  $HSi(C_2H_5)_2OCH_3$ ,

$\text{HSi}(\text{C}_6\text{H}_5)(\text{OCH}_3)_2$ ,  $\text{HSi}(\text{C}_6\text{H}_5)_2(\text{OCH}_3)$ ,  $\text{HSi}(\text{CH}_3)(\text{OC}(\text{O})\text{CH}_3)_2$ ,  
 $\text{HSi}(\text{CH}_3)_2\text{O}-[\text{Si}(\text{CH}_3)_2\text{O}]_2-\text{Si}(\text{CH}_3)(\text{OCH}_3)_2$ ,  $\text{HSi}(\text{CH}_3)[\text{O}-\text{N}=\text{C}(\text{CH}_3)_2]_2$   
 in each formula,  $\text{C}_6\text{H}_5$  represents a phenyl group, and so on.

- Among the hydrosilane compounds of the general formula  
 5 (8), hydrosilane compounds represented by the general formula:  
 $\text{H}-\text{Si}(\text{R}^{16})_{3-a}(\text{Y})_a$   
 in the formula,  $\text{R}^{16}$ , Y and a are as defined above,  
 are particularly preferred because of their ready availability.

- The vinyl polymer having the above-mentioned hydrolyzable  
 10 silyl group at a main chain terminus can be produced by the method  
 mentioned later herein.

- In causing the above-mentioned crosslinkable silyl  
 group-containing hydrosilane compound to add to a vinyl polymer  
 having an alkenyl group at a main chain terminus, a  
 15 hydrosilylation catalyst is used. This hydrosilylation  
 catalyst is not particularly restricted but may be a radical  
 initiator, such as an organic peroxide or azo compound, or a  
 transition metal catalyst, and so forth.

- The above radical initiator is not particularly restricted  
 20 but may be any of various ones, for example dialkyl peroxides  
 such as di-tert-butyl peroxide,  
 2,5-dimethyl-2,5-di(tert-butylperoxy)hexane,  
 2,5-dimethyl-2,5-di(tert-butylperoxy)-3-hexyne, dicumyl  
 peroxide, tert-butyl cumyl peroxide and  
 25  $\alpha, \alpha'$ -bis(tert-butylperoxy)isopropylbenzene, diacyl peroxides  
 such as benzoyl peroxide, p-chlorobenzoyl peroxide,  
 m-chlorobenzoyl peroxide, 2,4-dichlorobenzoyl peroxide and  
 lauroyl peroxide; peracid esters such as tert-butylperbenzoate;  
 peroxydicarbonates such as diisopropyl peroxydicarbonate and  
 30 di-2-ethylhexyl peroxydicarbonate; peroxyketals such as  
 1,1-di(tert-butylperoxy)cyclohexane and  
 1,1-di-(tert-butylperoxy)-3,3,5-trimethylcyclohexane.

- The above transition metal catalyst is not particularly  
 restricted but includes, simple substance platinum, solid  
 35 platinum dispersed on a carrier such as alumina, silica or carbon



black, chloroplatinic acid, chloroplatinic acid-alcohol, aldehyde or ketone complexes, platinum-olefin complexes, platinum(0)-divinyltetramethyldisiloxane complexes, and the like. As examples of the catalyst other than platinum compounds, there may be mentioned  $\text{RhCl}(\text{PPh}_3)_3$ ,  $\text{RhCl}_3$ ,  $\text{RuCl}_3$ ,  $\text{IrCl}_3$ ,  $\text{FeCl}_3$ ,  $\text{AlCl}_3$ ,  $\text{PdCl}_2 \cdot \text{H}_2\text{O}$ ,  $\text{NiCl}_2$ ,  $\text{TiCl}_4$  and the like. These catalysts may be used singly or two or more of them may be used in combination.

<Addition type curing>

Based on the vinyl polymer of the invention which has an alkenyl group at a main chain terminus, it is possible to prepare a curable composition comprising the same as a main component. Thus, the curable composition of the present invention comprises (A) the vinyl polymer of the present invention which has an alkenyl-terminated main chain and (B) a hydrosilyl group-containing compound.

The (A) component vinyl polymer may be used singly or two or more species may be used in admixture. The molecular weight of the (A) component is not particularly restricted but preferably is within the range of 500 to 100,000, more preferably within the range of 3,000 to 50,000. If it is less than 500, the characteristics intrinsic in vinyl polymers are hardly manifested and, if it is above 100,000, the viscosity becomes very high or the solubility becomes low, hence polymer handling becomes difficult.


The (B) component, namely hydrosilyl group-containing compound, is not particularly restricted but may be any of various ones. Thus, usable are linear polysiloxanes represented by the following general formula (9) or (10):



in the formula,  $\text{R}^{17}$  and  $\text{R}^{18}$  are the same or different and each represents an alkyl group containing 1 to 6 carbon atoms or a phenyl group,  $\text{R}^{19}$  represents an alkyl group containing 1 to 10



carbon atoms or an aralkyl group containing 7 to 10 carbon atoms, a represents an integer of 0 to 100, b represents an integer of 2 to 100 and c represents an integer of 0 to 100; and cyclic polysiloxanes represented by the following general formula (11):

5





in the formula,  $\text{R}^{17}$  and  $\text{R}^{18}$  each represents an alkyl group containing 1 to 6 carbon atoms or a phenyl group,  $\text{R}^{19}$  represents an alkyl group containing 1 to 10 carbon atoms or an aralkyl group containing 7 to 10 carbon atoms, d represents an integer of 0 to 8, e represents an integer of 2 to 10, f represents an integer of 0 to 8 and d, e and f satisfy the relation  $3 \leq d + e + f \leq 10$ .

These may be used singly or two or more of them may be used in admixture. Among these polysiloxanes, phenyl group-containing polysiloxanes are preferred in view of their compatibility with vinyl polymers. As examples of such compounds, there may be mentioned linear siloxanes represented by the general formula (12) or (13) given below and cyclic polysiloxanes represented by the general formula (14) or (15) given below:



in the formula,  $\text{R}^{20}$  represents a hydrogen or a methyl group, g represents an integer of 2 to 100, h represents an integer of 0 to 100 and  $\text{C}_6\text{H}_5$  is a phenyl group;




in the formula,  $\text{R}^{20}$  represents a hydrogen or a methyl group,  $i$  represents an integer of 2 to 10,  $j$  represents an integer of 0 to 8,  $i$  and  $j$  satisfy the relation  $3 \leq i + j \leq 10$  and  $\text{C}_6\text{H}_5$  is a phenyl group.

Further, as the (B) component hydrosilyl group-containing compounds, compounds obtainable by reacting a low-molecular compound having two or more alkenyl groups within the molecule with a polysiloxane represented by one of the above general formulas (9) to (15) in the manner of addition reaction so that the hydrosilyl groups may partly remain even after the reaction can be used. Various compounds can be used as the above low-molecular compound having two or more alkenyl groups. As examples, there may be mentioned hydrocarbon compounds such as 1,4-pentadiene, 1,5-hexadiene, 1,6-heptadiene, 1,7-octadiene, 1,8-nonadiene and 1,9-decadiene; ether compounds such as O,O'-diallylbisphenol A and 3,3'-diallylbisphenol A; ester compounds such as diallyl phthalate, diallyl isophthalate, triallyl trimellitate and tetraallyl pyromellitate; and carbonate compounds such as diethylene glycol diallyl carbonate, and so forth.

Such compounds can be prepared by adding a small amount of the above alkenyl group-containing low-molecular compound

- dropwise slowly to the polysiloxane represented by one of the general formulas (14) to (20) in the presence of a hydrosilylation catalyst. Among such compounds, those compounds shown below are preferred in view of the ready availability of raw materials,
- 5 the ready removability of the hydrosilyl group-containing compound used in excess and the compatibility with the (A) component vinyl polymer.



- 10 in above formulas, n is 2, 3 or 4 and m is an integer of 5 to 10.

- In the curable composition of the present invention, the vinyl polymer (A) and hydrosilyl group-containing compound (B) can be mixed together in arbitrary proportions. From the
- 15 curability viewpoint, however, the mole ratio between the alkenyl group and hydrosilyl group is preferably within the range of 0.2 to 5, more preferably 0.4 to 2.5. If that ratio is above

5, curing becomes insufficient and sticky curing products low in strength can only be obtained. If it is less than 0.2, a large amount of the active hydrosilyl group remains in curing products even after curing, causing cracking or void formation, hence no uniform and strong curing products can be obtained.

The curing reaction between the component (A) and the component (B) proceeds with mixing and heating two components. For accelerating the reaction, a hydrosilylation catalyst may further be added. Such hydrosilylation catalyst is not particularly restricted but maybe any of those already mentioned hereinabove. The catalyst amount is not particularly restricted but preferably is within the range of  $10^{-1}$  to  $10^{-8}$  mole, more preferably within the range of  $10^{-3}$  to  $10^{-6}$  mole, per mole of the alkenyl group in the component (A). If it is less than  $10^{-8}$  mole, curing will not proceed to a satisfactory extent. Since the hydrosilylation catalyst is expensive, it is preferred that it be not used in an amount exceeding  $10^{-1}$  mole.

When, in the above curable composition, the two components (A) and (B) are mixed up, if necessary together with the above-mentioned hydrosilylation catalyst, to thereby allow the curing to proceed, uniform curing products excellent in depth curability can be obtained without such an accompanying phenomenon as foaming. The curing conditions are not particularly restricted but, recommendably, the curing is generally carried out at  $0^{\circ}\text{C}$  to  $200^{\circ}\text{C}$ , preferably at  $30^{\circ}\text{C}$  to  $150^{\circ}\text{C}$ , for 10 seconds to 24 hours. At a high temperature of  $80^{\circ}\text{C}$  to  $150^{\circ}\text{C}$ , some compositions may cure in a period as short as 10 seconds to about an hour. The properties of the curing products depend on the main chain skeleton or molecular weight of the vinyl polymer (A) and of the hydrosilyl group-containing compound (B), and products widely ranging from rubber-like to resinous ones can be formed. As specific uses of the curing products obtainable from the above curable composition, there may be mentioned, for example, sealing materials, adhesives, pressure-sensitive adhesives, elastic adhesives, coatings,

powder coatings, foamed or expanded articles, potting agents for use in electric and electronic industries, films, gaskets, various molding materials, artificial marble and the like.

<Condensation type curable composition>

5 In the practice of the present invention, a curable composition comprising the above-mentioned crosslinkable silyl group-containing vinyl polymer as a main component can also be prepared. By treating the halogen group by the method of the present invention, it is possible to improve the storage  
10 stability of the above curable composition and to prevent various materials (in particular metals and, further, materials for use in electric or electronic industries) coming into contact with the curable composition from being corroded.

In this curable composition, the main component, namely  
15 the vinyl polymer having a crosslinkable silyl group at a main chain terminus, may comprise a single species or a mixture of two or more species. The molecular weight thereof is not particularly restricted but is preferably within the range of 500 to 100,000, more preferably within the range of 3,000 to  
20 50,000. If it is less than 500, the characteristics intrinsic in vinyl polymers having a crosslinkable silyl group at a main chain terminus are hardly manifested and, if it is above 100,000, polymer handling becomes difficult.

The vinyl polymer having a crosslinkable silyl group at  
25 a main chain terminus, when it comes into contact with water or moisture, undergoes a crosslinking reaction and becomes three-dimensional, hence is cured. Since the rate of hydrolysis varies depending on the temperature, humidity and crosslinkable silyl group species, an appropriate crosslinkable silyl group  
30 should be selected according to the use conditions. In storing the vinyl polymer having a crosslinkable silyl group at a main chain terminus, it is necessary to avoid the contact with moisture as far as possible.

For promoting the curing reaction of the above curable  
35 composition, a curing catalyst may be added. The catalyst



includes alkyl titanates, organosilicon titanates; carboxylic acid metal salts such as stannous octylate and dibutyltin dilaurate; and amine salts such as dibutylamine 2-ethylhexanoate, and so forth. Other acidic and basic catalysts can also be used.

- 5 The level of addition thereof is not particularly restricted but is preferably 0.01 to 5% by weight relative to the vinyl polymer having a crosslinkable silyl group at a main chain terminus.

- When the above curing catalyst is admixed as necessary  
10 with the vinyl polymer having a crosslinkable silyl group at a main chain terminus, which is the main component, and curing is allowed to proceed, uniform curing products can be obtained. The curing conditions are not particularly restricted but, generally, curing is effected at 0 to 100°C, preferably 10 to  
15 50°C, for about 1 hour to about 1 week. While the properties of the curing products depend on the main chain skeleton or molecular weight of the polymer used, a wide variety of products, from rubber-like ones to resinous ones, can be produced.

- As specific uses of the above curing products, there may  
20 be mentioned sealing materials, adhesives, pressure-sensitive adhesives, elastic adhesives, coatings, powder coatings, foamed articles, potting agents for use in electric and electronic industries, films, gaskets, various molding materials, artificial marble and the like.

25

#### BEST MODES FOR CARRYING OUT THE INVENTION

- In the following, typical examples of this invention are described together with certain comparative examples. The following examples, however, are by no means limitative of the  
30 scope of the present invention.

In the following examples and comparative examples, "part(s)" and "%" indicate "part(s) by weight" and "% by weight", respectively.

- In the following examples, the "number average molecular  
35 weight" and "molecular weight distribution (ratio of weight

average molecular weight to number average molecular weight)" were calculated by the standard polystyrene equivalent method using gel permeation chromatography (GPC). The GPC column used was one packed with a crosslinked polystyrene gel (Shodex GPC K-804; product of Showa Denko) and the GPC solvent used was chloroform.

(Production Example 1) (Example of production of a vinyl polymer having both an alkenyl group and a halogen group)

A 2-liter separable flask equipped with a reflux condenser and a stirrer was charged with CuBr (8.4 g, 58.5 mmol) and the reaction vessel inside was purged with nitrogen. Acetonitrile (112 mL) was added, and the mixture was stirred at 70°C on an oil bath for 30 minutes. Thereto were added butyl acrylate (200 g), diethyl 2,5-dibromoadipate (35.1 g, 97.5 mmol) and pentamethyldiethylenetriamine (hereinafter referred to as "triamine") (1.0 mL, 0.84 g, 4.9 mmol), and the reaction was thus started. While heating at 70°C with stirring, butyl acrylate (800 g) was added dropwise continuously over 2.5 hours. During dropping of butyl acrylate, triamine (1.0 mL) was supplemented. After the lapse of 4.5 hours after starting the reaction, 1,7-octadiene (144 mL, 107 g, 975 mmol) was added and, then, heating at 70°C was continued with stirring for 19 hours.

The reaction mixture was diluted with toluene, the dilution was passed through an activated alumina column and the volatile matter was distilled off under reduced pressure to give an alkenyl-terminated polymer (polymer [1]). The polymer [1] had a number average molecular weight of 13,300 and a molecular weight distribution of 1.29.

Elemental analysis revealed the bromine content in polymer [1] to be 1.1%.

(Example 1) (Example of Br treatment)

A 2-liter round-bottom flask equipped with a reflux condenser was charged with the polymer [1] (500 g), potassium

benzoate (24 g) and N,N-dimethylacetamide (500 mL), and the mixture was heated at 70°C with stirring under a nitrogen stream for 11 hours. The N,N-dimethylacetamide was distilled off under reduced pressure, and the residue was then diluted with toluene.

- 5 The toluene-insoluble solid matter (KBr and excess potassium benzoate) was filtered off through an activated alumina column. The volatile matter was distilled off from the filtrate under reduced pressure to give a polymer (polymer [2]).

Elemental analysis revealed the bromine content in polymer  
10 [2] to be 0.1%.

(Example 2) (Example of polymer purification)

- A 2-liter round-bottom flask equipped with a reflux condenser was charged with the polymer [2] (500 g), aluminum  
15 silicate (50 g, product of Kyowa Chemical, Kyowaad 700 PEL) and toluene (1.5 L), and the mixture was heated at 100°C with stirring under a nitrogen stream for 3 hours. The aluminum silicate was filtered off and the toluene was distilled off from the filtrate under reduced pressure to give a polymer [3].

20

(Example 3) (Alkenyl group silylation reaction)

- The polymer [3] was used as a Br-deprived polymer. A 1-liter pressure reactor was charged with the polymer [3] (315 g), dimethoxymethylhydrosilane (14.9 mL, 0.12 mol), dimethyl  
25 orthoformate (4.4 mL, 0.04 mmol) and the platinum(0)-1,1,3,3-tetramethyl-1,3-divinyl-disiloxane complex. The platinum catalyst was used in an amount of  $5 \times 10^{-4}$  equivalents per mole of the alkenyl group in the polymer. The reaction mixture was heated at 100°C for 1 hour. The volatile  
30 matter was distilled off from the mixture under reduced pressure to give a silyl-terminated polymer (polymer [4]). It was confirmed by  $^1\text{H}$  NMR analysis that the alkenyl group of polymer [1] had been completely disappeared and the silylation had occurred.

35

The polymer [4] was stored in a container at 25°C for 1

week. No gelation occurred and the fluidity was maintained. Thus, the storage stability was improved by treating the bromine group in the polymer.

5 (Comparative Example 1)

In lieu of the polymer [2] in Example 2, the polymer [1] was used as a polymer not yet deprived of Br. A polymer [5] was obtained in the same manner except that polymer [1] was used in lieu of polymer [2].

10

(Comparative Example 2)

Alkenyl group silylation was carried out in the same manner as in Example 3 except that the polymer [5] was used in lieu of the polymer [3] to give a silyl group-terminated polymer (polymer [6]). The polymer [6] gelled immediately after isolation, however.

15

(Production Example 2)

A 2-liter separable flask equipped with a reflux condenser and a stirrer was charged with CuBr (22.4 g, 156 mmol) and the reaction vessel inside was purged with nitrogen. Acetonitrile (112 mL) was added, and the mixture was stirred at 70°C on an oil bath for 30 minutes. Thereto were added butyl acrylate (200 g), methyl 2-bromopropionate (86.9 g, 520 mmol) and pentamethyldiethylenetriamine (hereinafter referred to as "triamine") (0.19 mL, 0.18 g, 1.0 mmol), and the reaction was thus started. While heating at 70°C with stirring, butyl acrylate (800 g) was added dropwise continuously over 150 minutes. During polymerization, the triamine (1.8 mL) was added in divided portions. After the lapse of 520 minutes after starting the reaction, the polymerization was terminated.


25

30

35

The reaction mixture was diluted with toluene, the dilution was passed through an activated alumina column and the volatile matter was distilled off under reduced pressure to give a poly(butyl acrylate) polymer having a Br group as represented

by the formula shown below at one terminus (polymer [7]). The polymer [7] had a number average molecular weight of 2,600 and a molecular weight distribution of 1.21.



5

(Example 4)

A 2-liter separable flask equipped with a reflux condenser and a stirrer was charged with the polymer [7] (940 g), potassium acetate (73.5 g) and N,N-dimethylacetamide (800 mL), and the mixture was heated at 70°C with stirring under a nitrogen stream for 3 hours. The N,N-dimethylacetamide was distilled off under reduced pressure, and the residue was then diluted with toluene. The toluene-insoluble solid matter (KBr and excess potassium acetate) was filtered off through an activated alumina column. The volatile matter was distilled off from the filtrate under reduced pressure to give a polymer [8].

10

15

(Example 5)

A silyl group-terminated polymer produced in the same manner as in Example 3 (Mn=23,300, molecular weight distribution 1.39, 50 g) and the polymer [8] (25 g) were admixed with 0.5 g each of two antioxidants (Irganox 1010 and Tinuvin 213; products of Ciba Specialty Chemicals), 0.5 g of a dehydrating agent (A-171; product of Nippon Unicar) and 1 g of a curing agent (U-220; product of Nitto Chemical) and the composition thus prepared under dehydrating conditions was stored at 50°C. Even after 4 weeks, it was stable without showing any sign of gelation.

20

25

(Comparative Example 3)

A composition was prepared in the same manner as in Example 5 except that the polymer [7] was used in lieu of the polymer [8] and stored at 50°C. After 4 weeks, it gelled.

30

(Production Example 3) (Copolymer production)

A 10-liter separable flask equipped with a reflux condenser

35

and a stirrer was charged with CuBr (36.02 g, 0.2511 mmol) and the reaction vessel inside was purged with nitrogen. Acetonitrile (618 mL) was added, and the mixture was stirred at 70°C on an oil bath for 15 minutes. Thereto were added butyl acrylate (360 mL, 2.51 mol), ethyl acrylate (500 mL, 4.62 mol), 2-methoxyethyl acrylate (375 mL, 2.91 mol), diethyl 2,5-dibromoadipate (150.68 g, 0.419 mol) and pentamethyldiethylenetriamine (hereinafter referred to as "triamine") (2.18 mL, 1.81 g, 10.46 mmol), and the reaction was thus started. While heating at 70°C with stirring, a mixture composed of butyl acrylate (1,440 mL), ethyl acrylate (2,002 mL) and 2-methoxyethyl acrylate (1,498 mL) was added dropwise continuously over 210 minutes. During dropping of the monomers, the triamine (7.63 mL, 6.33 g, 36.5 mmol) was supplemented. After the lapse of 330 minutes after starting the reaction, 1,7-octadiene (1,236 mL, 922 g, 8.37 mol) and the triamine (26.16 mL, 21.71 g, 0.125 mol) were added and, then, heating at 70°C was continued with stirring for 250 minutes.

The reaction mixture was diluted with toluene and the dilution was passed through an activated alumina column and the volatile matter was distilled off under reduced pressure to give an alkenyl-terminated copolymer {alkenyl-terminated poly(butyl acrylate/ethyl acrylate/methoxyethyl acrylate) copolymer; copolymer [9]}.

(Example 6)

A 10-liter separable flask equipped with a reflux condenser was charged with the copolymer [9] (2.87 kg), potassium acetate (79.57 g) and N,N-dimethylacetamide (2.9 L), and the mixture was heated at 100°C with stirring under a nitrogen stream for 12 hours. The N,N-dimethylacetamide was distilled off by heating under reduced pressure, and the residue was then diluted with toluene. The toluene-insoluble solid matter (KBr and excess potassium acetate) was filtered off through an activated alumina column. The volatile matter was distilled off from the

filtrate under reduced pressure to give a copolymer [10].

A 10-liter separable flask equipped with a reflux condenser was charged with the copolymer [10] (2.87 kg), acidic aluminum silicate (143 g, product of Kyowa Chemical, Kyowaad 700 SL),  
 5 basic aluminum silicate (143 g, product of Kyowa Chemical, Kyowaad 500 SH) and toluene (5.2 L), and the mixture was heated at 100°C with stirring under a nitrogen stream for 7 hours. The aluminum silicate was filtered off and the toluene was distilled off from the filtrate under reduced pressure to give a  
 10 vinyl-terminated copolymer (copolymer [11]). The copolymer obtained had a number average molecular weight of 18,000 as determined by GPC (on the polystyrene equivalent basis) and a molecular weight distribution of 1.24. The number of vinyl groups as introduced per copolymer molecule was determined by  
 15 <sup>1</sup>H NMR analysis and found to be 2.2.

(Example 7) (Addition type curing)

The copolymer [3] (20 g) obtained in Example 6 was admixed with 1.54 g of a linear siloxane (containing 5 (on average)  
 20 hydrosilyl groups and 5 (on average) α-methylstyrene groups in each molecule; Si-H group content 3.70 mmol/g) as a curing agent. To this mixture was added the  
 bis(1,3-divinyl-1,1,3,3-tetramethyldisiloxane)platinum  
 complex catalyst ( $1.32 \times 10^{-5}$  mmol/μl, xylene solution) as a  
 25 curing catalyst. After thorough mixing, the resulting curable composition was heated in an oven at 150°C. The composition quickly cured and gave a rubber-like curing product.

#### INDUSTRIAL APPLICABILITY

30 According to the present invention, the terminal halogen group of a vinyl polymer can be treated with ease. As a result, the storage stability of the polymer itself or of a curable composition comprising the polymer can be improved and reaction apparatus and various materials coming into contact with the  
 35 polymer can be prevented from being corroded. In particular,

the storage stability of a crosslinkable silyl group-containing polymer can be markedly improved.

111  
112  
113  
114  
115  
116  
117  
118  
119  
120  
121  
122  
123  
124  
125  
126  
127  
128  
129  
130  
131  
132  
133  
134  
135  
136  
137  
138  
139  
140  
141  
142  
143  
144  
145  
146  
147  
148  
149  
150  
151  
152  
153  
154  
155  
156  
157  
158  
159  
160  
161  
162  
163  
164  
165  
166  
167  
168  
169  
170  
171  
172  
173  
174  
175  
176  
177  
178  
179  
180  
181  
182  
183  
184  
185  
186  
187  
188  
189  
190  
191  
192  
193  
194  
195  
196  
197  
198  
199  
200  
201  
202  
203  
204  
205  
206  
207  
208  
209  
210  
211  
212  
213  
214  
215  
216  
217  
218  
219  
220  
221  
222  
223  
224  
225  
226  
227  
228  
229  
230  
231  
232  
233  
234  
235  
236  
237  
238  
239  
240  
241  
242  
243  
244  
245  
246  
247  
248  
249  
250  
251  
252  
253  
254  
255  
256  
257  
258  
259  
260  
261  
262  
263  
264  
265  
266  
267  
268  
269  
270  
271  
272  
273  
274  
275  
276  
277  
278  
279  
280  
281  
282  
283  
284  
285  
286  
287  
288  
289  
290  
291  
292  
293  
294  
295  
296  
297  
298  
299  
300  
301  
302  
303  
304  
305  
306  
307  
308  
309  
310  
311  
312  
313  
314  
315  
316  
317  
318  
319  
320  
321  
322  
323  
324  
325  
326  
327  
328  
329  
330  
331  
332  
333  
334  
335  
336  
337  
338  
339  
340  
341  
342  
343  
344  
345  
346  
347  
348  
349  
350  
351  
352  
353  
354  
355  
356  
357  
358  
359  
360  
361  
362  
363  
364  
365  
366  
367  
368  
369  
370  
371  
372  
373  
374  
375  
376  
377  
378  
379  
380  
381  
382  
383  
384  
385  
386  
387  
388  
389  
390  
391  
392  
393  
394  
395  
396  
397  
398  
399  
400  
401  
402  
403  
404  
405  
406  
407  
408  
409  
410  
411  
412  
413  
414  
415  
416  
417  
418  
419  
420  
421  
422  
423  
424  
425  
426  
427  
428  
429  
430  
431  
432  
433  
434  
435  
436  
437  
438  
439  
440  
441  
442  
443  
444  
445  
446  
447  
448  
449  
450  
451  
452  
453  
454  
455  
456  
457  
458  
459  
460  
461  
462  
463  
464  
465  
466  
467  
468  
469  
470  
471  
472  
473  
474  
475  
476  
477  
478  
479  
480  
481  
482  
483  
484  
485  
486  
487  
488  
489  
490  
491  
492  
493  
494  
495  
496  
497  
498  
499  
500  
501  
502  
503  
504  
505  
506  
507  
508  
509  
510  
511  
512  
513  
514  
515  
516  
517  
518  
519  
520  
521  
522  
523  
524  
525  
526  
527  
528  
529  
530  
531  
532  
533  
534  
535  
536  
537  
538  
539  
540  
541  
542  
543  
544  
545  
546  
547  
548  
549  
550  
551  
552  
553  
554  
555  
556  
557  
558  
559  
560  
561  
562  
563  
564  
565  
566  
567  
568  
569  
570  
571  
572  
573  
574  
575  
576  
577  
578  
579  
580  
581  
582  
583  
584  
585  
586  
587  
588  
589  
590  
591  
592  
593  
594  
595  
596  
597  
598  
599  
600  
601  
602  
603  
604  
605  
606  
607  
608  
609  
610  
611  
612  
613  
614  
615  
616  
617  
618  
619  
620  
621  
622  
623  
624  
625  
626  
627  
628  
629  
630  
631  
632  
633  
634  
635  
636  
637  
638  
639  
640  
641  
642  
643  
644  
645  
646  
647  
648  
649  
650  
651  
652  
653  
654  
655  
656  
657  
658  
659  
660  
661  
662  
663  
664  
665  
666  
667  
668  
669  
670  
671  
672  
673  
674  
675  
676  
677  
678  
679  
680  
681  
682  
683  
684  
685  
686  
687  
688  
689  
690  
691  
692  
693  
694  
695  
696  
697  
698  
699  
700  
701  
702  
703  
704  
705  
706  
707  
708  
709  
710  
711  
712  
713  
714  
715  
716  
717  
718  
719  
720  
721  
722  
723  
724  
725  
726  
727  
728  
729  
730  
731  
732  
733  
734  
735  
736  
737  
738  
739  
740  
741  
742  
743  
744  
745  
746  
747  
748  
749  
750  
751  
752  
753  
754  
755  
756  
757  
758  
759  
760  
761  
762  
763  
764  
765  
766  
767  
768  
769  
770  
771  
772  
773  
774  
775  
776  
777  
778  
779  
780  
781  
782  
783  
784  
785  
786  
787  
788  
789  
790  
791  
792  
793  
794  
795  
796  
797  
798  
799  
800  
801  
802  
803  
804  
805  
806  
807  
808  
809  
810  
811  
812  
813  
814  
815  
816  
817  
818  
819  
820  
821  
822  
823  
824  
825  
826  
827  
828  
829  
830  
831  
832  
833  
834  
835  
836  
837  
838  
839  
840  
841  
842  
843  
844  
845  
846  
847  
848  
849  
850  
851  
852  
853  
854  
855  
856  
857  
858  
859  
860  
861  
862  
863  
864  
865  
866  
867  
868  
869  
870  
871  
872  
873  
874  
875  
876  
877  
878  
879  
880  
881  
882  
883  
884  
885  
886  
887  
888  
889  
890  
891  
892  
893  
894  
895  
896  
897  
898  
899  
900  
901  
902  
903  
904  
905  
906  
907  
908  
909  
910  
911  
912  
913  
914  
915  
916  
917  
918  
919  
920  
921  
922  
923  
924  
925  
926  
927  
928  
929  
930  
931  
932  
933  
934  
935  
936  
937  
938  
939  
940  
941  
942  
943  
944  
945  
946  
947  
948  
949  
950  
951  
952  
953  
954  
955  
956  
957  
958  
959  
960  
961  
962  
963  
964  
965  
966  
967  
968  
969  
970  
971  
972  
973  
974  
975  
976  
977  
978  
979  
980  
981  
982  
983  
984  
985  
986  
987  
988  
989  
990  
991  
992  
993  
994  
995  
996  
997  
998  
999  
1000  
1001  
1002  
1003  
1004  
1005  
1006  
1007  
1008  
1009  
1010  
1011  
1012  
1013  
1014  
1015  
1016  
1017  
1018  
1019  
1020  
1021  
1022  
1023  
1024  
1025  
1026  
1027  
1028  
1029  
1030  
1031  
1032  
1033  
1034  
1035  
1036  
1037  
1038  
1039  
1040  
1041  
1042  
1043  
1044  
1045  
1046  
1047  
1048  
1049  
1050  
1051  
1052  
1053  
1054  
1055  
1056  
1057  
1058  
1059  
1060  
1061  
1062  
1063  
1064  
1065  
1066  
1067  
1068  
1069  
1070  
1071  
1072  
1073  
1074  
1075  
1076  
1077  
1078  
1079  
1080  
1081  
1082  
1083  
1084  
1085  
1086  
1087  
1088  
1089  
1090  
1091  
1092  
1093  
1094  
1095  
1096  
1097  
1098  
1099  
1100  
1101  
1102  
1103  
1104  
1105  
1106  
1107  
1108  
1109  
1110  
1111  
1112  
1113  
1114  
1115  
1116  
1117  
1118  
1119  
1120  
1121  
1122  
1123  
1124  
1125  
1126  
1127  
1128  
1129  
1130  
1131  
1132  
1133  
1134  
1135  
1136  
1137  
1138  
1139  
1140  
1141  
1142  
1143  
1144  
1145  
1146  
1147  
1148  
1149  
1150  
1151  
1152  
1153  
1154  
1155  
1156  
1157  
1158  
1159  
1160  
1161  
1162  
1163  
1164  
1165  
1166  
1167  
1168  
1169  
1170  
1171  
1172  
1173  
1174  
1175  
1176  
1177  
1178  
1179  
1180  
1181  
1182  
1183  
1184  
1185  
1186  
1187  
1188  
1189  
1190  
1191  
1192  
1193  
1194  
1195  
1196  
1197  
1198  
1199  
1200  
1201  
1202  
1203  
1204  
1205  
1206  
1207  
1208  
1209  
1210  
1211  
1212  
1213  
1214  
1215  
1216  
1217  
1218  
1219  
1220  
1221  
1222  
1223  
1224  
1225  
1226  
1227  
1228  
1229  
1230  
1231  
1232  
1233  
1234  
1235  
1236  
1237  
1238  
1239  
1240  
1241  
1242  
1243  
1244  
1245  
1246  
1247  
1248  
1249  
1250  
1251  
1252  
1253  
1254  
1255  
1256  
1257  
1258  
1259  
1260  
1261  
1262  
1263  
1264  
1265  
1266  
1267  
1268  
1269  
1270  
1271  
1272  
1273  
1274  
1275  
1276  
1277  
1278  
1279  
1280  
1281  
1282  
1283  
1284  
1285  
1286  
1287  
1288  
1289  
1290  
1291  
1292  
1293  
1294  
1295  
1296  
1297  
1298  
1299  
1300  
1301  
1302  
1303  
1304  
1305  
1306  
1307  
1308  
1309  
1310  
1311  
1312  
1313  
1314  
1315  
1316  
1317  
1318  
1319  
1320  
1321  
1322  
1323  
1324  
1325  
1326  
1327  
1328  
1329  
1330  
1331  
1332  
1333  
1334  
1335  
1336  
1337  
1338  
1339  
1340  
1341  
1342  
1343  
1344  
1345  
1346  
1347  
1348  
1349  
1350  
1351  
1352  
1353  
1354  
1355  
1356  
1357  
1358  
1359  
1360  
1361  
1362  
1363  
1364  
1365  
1366  
1367  
1368  
1369  
1370  
1371  
1372  
1373  
1374  
1375  
1376  
1377  
1378  
1379  
1380  
1381  
1382  
1383  
1384  
1385  
1386  
1387  
1388  
1389  
1390  
1391  
1392  
1393  
1394  
1395  
1396  
1397  
1398  
1399  
1400  
1401  
1402  
1403  
1404  
1405  
1406  
1407  
1408  
1409  
1410  
1411  
1412  
1413  
1414  
1415  
1416  
1417  
1418  
1419  
1420  
1421  
1422  
1423  
1424  
1425  
1426  
1427  
1428  
1429  
1430  
1431  
1432  
1433  
1434  
1435  
1436  
1437  
1438  
1439  
1440  
1441  
1442  
1443  
1444  
1445  
1446  
1447  
1448  
1449  
1450  
1451  
1452  
1453  
1454  
1455  
1456  
1457  
1458  
1459  
1460  
1461  
1462  
1463  
1464  
1465  
1466  
1467  
1468  
1469  
1470  
1471  
1472  
1473  
1474  
1475  
1476  
1477  
1478  
1479  
1480  
1481  
1482  
1483  
1484  
1485  
1486  
1487  
1488  
1489  
1490  
1491  
1492  
1493  
1494  
1495  
1496  
1497  
1498  
1499  
1500  
1501  
1502  
1503  
1504  
1505  
1506  
1507  
1508  
1509  
1510  
1511  
1512  
1513  
1514  
1515  
1516  
1517  
1518  
1519  
1520  
1521  
1522  
1523  
1524  
1525  
1526  
1527  
1528  
1529  
1530  
1531  
1532  
1533  
1534  
1535  
1536  
1537  
1538  
1539  
1540  
1541  
1542  
1543  
1544  
1545  
1546  
1547  
1548  
1549  
1550  
1551  
1552  
1553  
1554  
1555  
1556  
1557  
1558  
1559  
1560  
1561  
1562  
1563  
1564  
1565  
1566  
1567  
1568  
1569  
1570  
1571  
1572  
1573  
1574  
1575  
1576  
1577  
1578  
1579  
1580  
1581  
1582  
1583  
1584  
1585  
1586  
1587  
1588  
1589  
1590  
1591  
1592  
1593  
1594  
1595  
1596  
1597  
1598  
1599  
1600  
1601  
1602  
1603  
1604  
1605  
1606  
1607  
1608  
1609  
1610  
1611  
1612  
1613  
1614  
1615  
1616  
1617  
1618  
1619  
1620  
1621  
1622  
1623  
1624  
1625  
1626  
1627  
1628  
1629  
1630  
1631  
1632  
1633  
1634  
1635  
1636  
1637  
1638  
1639  
1640  
1641  
1642  
1643  
1644  
1645  
1646  
1647  
1648  
1649  
1650  
1651  
1652  
1653  
1654  
1655  
1656  
1657  
1658  
1659  
1660  
1661  
1662  
1663  
1664  
1665  
1666  
1667  
1668  
1669  
1670  
1671  
1672  
1673  
1674  
1675  
1676  
1677  
1678  
1679  
1680  
1681  
1682  
1683  
1684  
1685  
1686  
1687  
1688  
1689  
1690  
1691  
1692  
1693  
1694  
1695  
1696  
1697  
1698  
1699  
1700  
1701  
1702  
1703  
1704  
1705  
1706  
1707  
1708  
1709  
1710  
1711  
1712  
1713  
1714  
1715  
1716  
1717  
1718  
1719  
1720  
1721  
1722  
1723  
1724  
1725  
1726  
1727  
1728  
1729  
1730  
1731  
1732  
1733  
1734  
1735  
1736  
1737  
1738  
1739  
1740  
1741  
1742  
1743  
1744  
1745  
1746  
1747  
1748  
1749  
1750  
1751  
1752  
1753  
1754  
1755  
1756  
1757  
1758  
1759  
1760  
1761  
1762  
1763  
1764  
1765  
1766  
1767  
1768  
1769  
1770  
1771  
1772  
1773  
1774  
1775  
1776  
1777  
1778  
1779  
1780  
1781  
1782  
1783  
1784  
1785  
1786  
1787  
1788  
1789  
1790  
1791  
1792  
1793  
1794  
1795  
1796  
1797  
1798  
1799  
1800  
1801  
1802  
1803  
1804  
1805  
1806  
1807  
1808  
1809  
1810  
1811  
1812  
1813  
1814  
1815  
1816  
1817  
1818  
1819  
1820  
1821  
1822  
1823  
1824  
1825  
1826  
1827  
1828  
1829  
1830  
1831  
1832  
1833  
1834  
1835  
1836  
1837  
1838  
1839  
1840  
1841  
1842  
1843  
1844  
1845  
1846  
1847  
1848  
1849  
1850  
1851  
1852  
1853  
1854  
1855  
1856  
1857  
1858  
1859  
1860  
1861  
1862  
1863  
1864  
1865  
1866  
1867  
1868  
1869  
1870  
1871  
1872  
1873  
1874  
1875  
1876  
1877  
1878  
1879  
1880  
1881  
1882  
1883  
1884  
1885  
1886  
1887  
1888  
1889  
1890  
1891  
1892  
1893  
1894  
1895  
1896  
1897  
1898  
1899  
1900  
1901  
1902  
1903  
1904  
1905  
1906  
1907  
1908  
1909  
1910  
1911  
1912  
1913  
1914  
1915  
1916  
1917  
1918  
1919  
1920  
1921  
1922  
1923  
1924  
1925  
1926  
1927  
1928  
1929  
1930  
1931  
1932  
1933  
1934  
1935  
1936  
1937  
1938  
1939  
1940  
1941  
1942  
1943  
1944  
1945  
1946  
1947  
1948  
1949  
1950  
1951  
1952  
1953  
1954  
1955  
1956  
1957  
1958  
1959  
1960  
1961  
1962  
1963  
1964  
1965  
1966  
1967  
1968  
1969  
1970  
1971  
1972  
1973  
1974  
1975  
1976  
1977  
1978  
1979  
1980  
1981  
1982  
1983  
1984  
1985  
1986  
1987  
1988  
1989  
1990  
1991  
1992  
1993  
1994  
1995  
1996  
1997  
1998  
1999  
2000  
2001  
2002  
2003  
2004  
2005  
2006  
2007  
2008  
2009  
2010  
2011  
2012  
2013  
2014  
2015  
2016  
2017  
2018  
2019  
2020  
2021  
2022  
2023  
2024  
2025  
2026  
2027  
2028  
2029  
2030  
2031  
2032  
2033  
2034  
2035  
2036  
2037  
2038  
2039  
2040  
2041  
2042  
2043  
2044  
2045  
2046  
2047  
2048  
2049  
2050  
2051  
2052  
2053  
2054  
2055  
2056  
2057  
2058  
2059  
2060  
2061  
2062  
2063  
2064  
2065  
2066  
2067  
2068  
2069  
2070  
2071  
2072  
2073  
2074  
2075  
2076  
2077  
2078  
2079  
2080  
2081  
2082  
2083  
2084  
2085  
2086  
2087  
2088  
2089  
2090  
2091  
2092  
2093  
2094  
2095  
2096  
2097  
2098  
2099  
2100  
2101  
2102  
2103  
2104  
2105  
2106  
2107  
2108  
2109  
2110  
2111  
2112  
2113  
2114  
2115  
2116  
2117  
2118  
2119  
2120  
2121  
2122  
2123  
2124  
2125  
2126  
2127  
2128  
2129  
2130  
2131  
2132  
2133  
2134  
2135  
2136  
2137  
2138  
2139  
2140  
2141  
2142  
2143  
2144  
2145  
2146  
2147  
2148  
2149  
2150  
2151  
2152  
2153  
2154  
2155  
2156  
2157  
2158  
2159  
2160  
2161  
2162  
2163  
2164  
2165  
2166  
2167  
2168  
2169  
2170  
2171  
2172  
2173  
2174  
2175  
2176  
2177  
2178  
2179  
2180  
2181  
2182  
2183  
2184  
2185  
2186  
2187  
2188  
2189  
2190  
2191  
2192  
2193  
2194  
2195  
2196  
2197  
2198  
2199  
2200  
2201  
2202  
2203  
2204  
2205  
2206  
2207  
2208  
2209  
2210  
2211  
2212  
2213  
2214  
2215  
2216  
2217  
2218  
2219  
2220  
2221  
2222  
2223  
2224  
2225  
2226  
2227  
2228  
2229  
2230  
2231  
2232  
2233  
2234  
2235  
2236  
2237  
2238  
2239  
2240  
2241  
2242  
2243  
2244  
2245  
2246  
2247  
2248  
2249  
2250  
2251  
2252  
2253  
2254  
2255  
2256  
2257  
2258  
2259  
2260  
2261  
2262  
2263  
2264  
2265  
2266  
2267  
2268  
2269  
2270  
2271  
2272  
2273  
2274  
2275  
2276  
2277  
2278  
2279  
2280  
2281  
2282  
2283  
2284  
2285  
2286  
2287  
2288  
2289  
2290  
2291  
2292  
2293  
2294  
2295  
2296  
2297  
2298  
2299  
2300  
2301  
2302  
2303  
2304



## CLAIMS

1. A production method of a vinyl polymer comprising treating a halogen group-containing vinyl polymer (I) with an oxy anion compound to thereby reduce the halogen content of the polymer.
2. The production method according to Claim 1, wherein the vinyl polymer (I) has a halogen group at a molecular chain terminus.
3. The production method according to Claim 1, wherein the vinyl polymer (I) has a functional group other than a halogen group in a terminal structure thereof in addition to the halogen group.
4. The production method according to Claim 3, wherein the functional group in the terminal structure of the vinyl polymer (I) is selected from the group consisting of alkenyl, hydroxyl, silyl, amino and epoxy groups.
5. The production method according to Claim 4, wherein the functional group in a terminal structure of the vinyl polymer (I) is an alkenyl group.
6. The production method according to Claim 5, wherein, when the vinyl polymer (I) has an alkenyl group in a terminal structure thereof, after the elimination of the halogen group by means of an oxy anion compound, a crosslinkable silyl group-containing hydrosilane compound is caused to be added to said alkenyl group.
7. The production method according to any of Claims 1 to 6, wherein the oxy anion compound has no functional group

other than an oxy anion group.


8. The production method according to any of Claims 1 to 7,

5 wherein the oxy anion compound has a group represented by the general formula 1:



in the formula,  $R^1$  represents an organic group, which may optionally contain one or more ether or ester linkages, and  $M^+$   
10 represents an alkali metal ion or a quaternary ammonium ion.

9. The production method according to Claim 8, wherein, in the general formula 1,  $R^1$  is an organic group represented by the following general formula 2:



in the formula,  $R^2$  represents an organic group, which may optionally contain one or more ether or ester linkages.

10. The production method according to Claim 8 or 9, wherein, in the general formula 1 or 2,  $R^1$  or  $R^2$  is a univalent or bivalent organic group.

11. The production method according to Claim 9 or 10, wherein, in the general formula 2,  $R^2$  is an aromatic group.

12. The production method according to any of Claims 8 to 11, wherein, in the general formula 1,  $M^+$  is a potassium ion.

13. The production method according to any of Claims 1 to 7,

wherein the oxy anion compound comprises at least one salt selected from the group consisting of alkoxide salts, phenoxide salts and carboxylate salts, and the counter ion thereto is an  
35 alkali metal ion or a quaternary ammonium ion.

14. The production method according to Claim 13,  
wherein the oxy anion compound is a univalent or bivalent  
carboxylate salt.

5

15. The production method according to Claim 13,  
wherein the oxy anion compound is derived from any of  
benzoic acids or an acetic acid.

10

16. The production method according to any of Claims  
1 to 15,

wherein the vinyl polymer (I) is produced by atom transfer  
radical polymerization.

15

17. The production method according to Claim 16,  
wherein the terminal halogen group of the vinyl polymer  
(I) has a structure represented by the general formula 3:



in the formula,  $R^3$  and  $R^4$  are the same or different and each  
represents a hydrogen atom or a univalent organic group  
respectively derived from a group bound to a polymerizable  
carbon-carbon double bond group in the vinyl monomer constituting  
said polymer, and X represents a chlorine, bromine or iodine.

25

18. The production method according to Claim 16,  
wherein, in atom transfer radical polymerization, the  
terminal halogen group of the vinyl polymer (I) is a halogen  
group resulting from addition of an olefin compound having low  
polymerizability to a polymer terminus upon addition of the  
olefin compound during or at the end of the polymerization.

30

19. The production method according to any of Claims  
1 to 18,

wherein a main chain of the vinyl polymer (I) is a  
(meth)acrylic polymer.

35

20. The production method according to Claim 19,  
wherein the main chain of the vinyl polymer (I) is an acrylic  
polymer.

21. The production method according to any of Claims  
1 to 18,  
wherein the main chain of the vinyl polymer (I) is a styrenic  
polymer.

22. The production method according to any of Claims  
1 to 21,  
wherein a ratio ( $M_w/M_n$ ) between weight average molecular  
weight ( $M_w$ ) and number average molecular weight ( $M_n$ ) of the vinyl  
polymer (I) is less than 1.8 as determined by gel permeation  
chromatography.

23. The production method according to any of Claims  
1 to 22,  
wherein the number average molecular weight of the vinyl  
polymer (I) is within the range of 500 to 100,000.

24. A vinyl polymer  
which is producible by the production method according  
to any of Claims 1 to 23.

25. A curable composition  
which comprises the vinyl polymer according to Claim 24  
having a crosslinkable silyl group in a terminal structure  
thereof.

26. A curable composition  
which comprises (A) the vinyl polymer according to Claim  
24 having an alkenyl group in a terminal structure thereof and  
(B) a hydrosilyl group-containing compound.

**DECLARATION FOR U.S. PATENT APPLICATION**

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

**METHOD OF TREATING POLYMER**

the specification of which is attached hereto unless the following is checked

☒ was filed on April 3, 2000 as PCT International Application Number PCT/JP00/02158 and filed on \_\_\_\_\_ as United States Application Number \_\_\_\_\_ amended on \_\_\_\_\_ (if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claim(s), as amended by any amendment referred above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, § 119 (a) - (d) of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application for which priority is claimed.

**Priority Claimed**

List prior foreign applications. See note A on back of this page

<u>11/95656</u> (Number)	<u>JAPAN</u> (Country)	<u>02/04/1999</u> (Day/Month/Year Filed)	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No
<u>                    </u> (Number)	<u>                    </u> (Country)	<u>                    </u> (Day/Month/Year Filed)	<input type="checkbox"/> Yes <input type="checkbox"/> No
<u>                    </u> (Number)	<u>                    </u> (Country)	<u>                    </u> (Day/Month/Year Filed)	<input type="checkbox"/> Yes <input type="checkbox"/> No
<u>                    </u> (Number)	<u>                    </u> (Country)	<u>                    </u> (Day/Month/Year Filed)	<input type="checkbox"/> Yes <input type="checkbox"/> No

(See note B on back of this page)

☐ See attached list for additional prior foreign applications

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

**Status**

(List prior U.S. Applications)

<u>                    </u> (Application Serial No.)	<u>                    </u> (Filing Date)	<input type="checkbox"/> Patented <input type="checkbox"/> Pending <input type="checkbox"/> Abandoned
<u>                    </u> (Application Serial No.)	<u>                    </u> (Filing Date)	<input type="checkbox"/> Patented <input type="checkbox"/> Pending <input type="checkbox"/> Abandoned
<u>                    </u> (Application Serial No.)	<u>                    </u> (Filing Date)	<input type="checkbox"/> Patented <input type="checkbox"/> Pending <input type="checkbox"/> Abandoned

I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:



23850

PATENT TRADEMARK OFFICE

Please direct all communications to the following address:



23850

PATENT TRADEMARK OFFICE

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Title 18 of the United States Code, § 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

(See note C)

100 Full name of sole or first inventor (given name, family name) Yoshiki NAKAGAWA  
Inventor's signature *Yoshiki Nakagawa* Date JAN. 24, 2002  
Residence Kobe-shi, Japan JPN Citizenship Japanese

Post Office Address c/o Kobe Research Laboratories Performance Materials R&D Center of Kaneka Corporation  
2-80, Yoshidacho 1-chome, Hyogo-ku, Kobe-shi, HYOGO 652-0872 JAPAN

200 Full name of second inventor (given name, family name) Kenichi KITANO  
Inventor's signature *Kenichi Kitano* Date JAN. 24, 2002  
Residence Kobe-shi, Japan JPN Citizenship Japanese

Post Office Address c/o Kobe Research Laboratories Performance Materials R&D Center of Kaneka Corporation  
2-80, Yoshidacho 1-chome, Hyogo-ku, Kobe-shi, HYOGO 652-0872 JAPAN

300 Full name of third inventor (given name, family name) Nao FUJITA  
Inventor's signature *Nao Fujita* Date JAN. 24, 2002  
Residence Kobe-shi, Japan JPN Citizenship Japanese

Post Office Address c/o Kobe Research Laboratories Performance Materials R&D Center of Kaneka Corporation  
2-80, Yoshidacho 1-chome, Hyogo-ku, Kobe-shi, HYOGO 652-0872 JAPAN

Full name of fourth inventor (given name, family name) \_\_\_\_\_  
Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_  
Residence \_\_\_\_\_ Citizenship \_\_\_\_\_  
Post Office Address \_\_\_\_\_

Full name of fifth inventor (given name, family name) \_\_\_\_\_  
Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_  
Residence \_\_\_\_\_ Citizenship \_\_\_\_\_  
Post Office Address \_\_\_\_\_

